A sharp-interface theory for spherulitic crystallization in binary thin films under solvent-vapor annealing

Michel Jabbour* and Chi-Sing Man†

Department of Mathematics, University of Kentucky, Lexington, KY 40506-0027, USA

Roberto Paroni‡

Dipartimento di Architettura e Pianificazione, Università di Sassari, 07041 Alghero, Italy

Blending organic small-molecule semiconductors as donor-acceptor and host-guest pairs would allow the low-cost solution processing of large areas of photovoltaic cells and thin-film transistors. To improve the charge-carrier mobilities of transistors and power-conversion efficiencies of solar cells, the host in the former and both donor and acceptor in the latter should be crystalline and the regions they occupy be given suitable sizes and morphologies. Solvent-vapor annealing of spin-coated, amorphous, binary thin-film blends is a promising means for the achievement of these goals. Under vapor annealing nuclei of organic semiconductors grow as spherulites, whose radii increase at constant rate for a given temperature, solvent-vapor pressure, and substrate. Here we present a thermodynamically consistent theory of solvent-vapor induced spherulitic crystallization in blended thin films, which delivers constant growth rate. Under the proposed theory, spherulitic growth is interface driven, with no diffusion of any species. As quantitative experimental data on spherulitic growth rates are available for binary films with a major and a minor component (referred to as the solute and the additive, respectively), we derive formulas which show how the mole fraction of the additive affects spherulitic growth rates in such films when the solute and additive remain in solution within the spherulitic phase and when they become segregated there.

I. INTRODUCTION

A. Background

Organic photovoltaics (OPVs), thin-film transistors (OTFTs), and light-emitting diodes (OLEDs), which are solution processable at near-ambient temperatures, offer the possibility of large-area and inexpensive fabrication on flexible structures by the use of high-speed printing technologies [1, 2]. This advantage notwithstanding, for OPVs and OTFTs to be competitive with their inorganic counterparts in widespread adoption, their power conversion efficiencies and device mobilities, respectively, will have to be improved.

Organic small-molecule semiconductors have attractive features for application in OPVs, OTFTs, and OLEDs [2–6]. As pointed out by Lloyd *et al.* [6], “[t]hey offer the facile processing associated with polymers, yet are easier to synthesize and purify, are monodisperse, and typically show higher charge carrier mobilities.” In recent years, binary blends of organic semiconducting small molecules have been actively studied as the host-guest pair in OTFTs and as the donor-acceptor pair in bulk heterojunction OPVs [7, 8].

Device performance, as measured by the power conversion efficiency of OPVs and the field-effect mobility of OTFTs, is known to be improved by solvent-vapor annealing [7, 9–14]. For thin-film blends of small-molecule

semiconductors which are formed by spin coating and are largely amorphous in the as-spun state, film restructuring upon exposition to solvent vapor often proceeds by crystallization through heterogeneous nucleation and spherulitic growth. Examples of such thin-film blends include (6,6)-phenyl C₆₁ butyric acid methyl ester (PCBM) and 2,8-diethyl-5,11-bis(triethylsilylethynyl) anthradithiophene (ethyl-TES ADT) in bulk heterojunction OPVs [7] and triethylsilylethynyl anthradithiophene (TES ADT) with various additives in OTFTs [9, 16]. However, as observed by Hedge *et al.* [15], the thermodynamic driving forces that lead to morphology changes during annealing treatments and the evolution of microstructure with solvent exposure have not yet been identified, irrespective of whether growth is spherulitic or otherwise. Clarifying the physics of heterogeneous nucleation and spherulitic growth in binary, solution-processed, organic semiconductor thin films under solvent-vapor annealing is therefore crucial for further advancement of research on the subject.

Spherulites are densely branched aggregates of crystalline fibers, whose macroscopic shape in two space dimensions is that of a disk. They are found in a variety of materials, including metallic glasses [18, 19], minerals [20, 21], high polymers [22], organic compounds [23], and liquid crystals [24]. Keith and Padden [25] observed that spherulites which crystallize in materials possessing widely distinct chemical structures and physical properties are characterized by identical morphologies and growth kinetics. They concluded that it should be possible to account for the mechanisms that govern spherulitic growth in terms sufficiently general as to apply to all known types of spherulite-forming systems. Later an attempt was made by Goldenfeld [26] to quantify the

*Electronic address: jabbour@ms.uky.edu

†Electronic address: chi-sing.man@uky.edu

‡Electronic address: paroni@uniss.it

qualitative arguments put forward by Keith and Padden. In the resulting sharp-interface theory of Goldenfeld, as well as in the phase-field model proposed by Gránásky *et al.* [27], impurities are expelled from the spherulitic region as it crystallizes and diffuse away from the interface into the mother phase. In place of the classical Gibbs–Thomson relation, which specifies the impurity concentration at the phase boundary, Goldenfeld postulates a kinetic relation that delivers the growth rate as a linear function of the jump in chemical potential of the impurity species across the interface.

B. Main results

In this paper we restrict our attention to the isothermal crystallization of an isolated spherulite in a binary thin-film blend under solvent-vapor annealing. We derive a simple sharp-interface theory that predicts the growth, under a given set of experimental conditions, of the spherulite at a constant rate and can account for the available data on growth rates in single-component (TES ADT) and binary (TES ADT doped with one of several additives) small-molecule semiconductor films under solvent-vapor annealing (see Supporting Information of Lee *et al.* [8], Section 2; Supporting Information of Lee *et al.* [16]; Loo [17]).

In contrast to existing theories of spherulitic growth, ours is interface-driven, with no diffusion of any species. As a result of the presence of residual amounts of solvent in the film and at the interface separating it from the substrate throughout the crystallization process, the stress in both amorphous and crystalline phases is assumed to remain spherical and the contact between film and substrate is considered to be smooth. The theory is thermodynamically consistent in the sense that all constitutive relations are compatible with the first and second laws. Its main result is a kinetic relation (72) linking the migrational velocity of the crystallization front to the driving force, which is identified with the conjugate of the migrational velocity in the interfacial dissipation inequality, thus addressing an outstanding gap in the literature pointed out by Hegde *et al.* [15].

Under the adherence boundary condition at the interface between the film and the vapor, the interfacial momentum balance reduces to the Young–Laplace condition. In this case, the driving force for spherulitic crystallization can be written in terms of the jumps in the chemical potentials of the two constituents of the binary film and of the solvent, measured relative to their values in the vapor phase. Moreover, when the two species in question are involatile, we present a physically plausible scenario under which we obtain from the aforementioned kinetic relation the prediction of constant interfacial velocity, which is a central feature of spherulitic crystallization; see the paragraph that follows (106). This result applies to experiments in which annealing is driven either by the residual solvent present in a film after spin coat-

ing [7] or upon exposure to solvent vapor of a film which has been thermally annealed after spin coating [17].

Finally, for films with a major component (the solute) and a minor one (the additive), we distinguish between the following two scenarios. When the solute and additive are in solid solution inside of the spherulitic region, we show that the dependence of the growth rate on the mole fraction of additive is linear, in agreement with the experimental data of Lee *et al.* [8] on the crystallization rate in thin-film blends of TES ADT with some additives. Alternatively, if the additive and solute become unmixed in the spherulite, we establish that the growth rate drops abruptly in the vicinity of zero additive mole fraction, a prediction that is consistent with measurements on films of TES ADT and several other additives [17, 28].

C. Organization

The remainder of this paper is organized as follows. In Section II, two transport identities are presented, whose derivation we relegate to Appendix A. These identities are instrumental in obtaining the field equations and jump conditions on which the theory rests. Mass and momentum balances are discussed in Sections III and IV, respectively, with the tangential character of the interfacial Cauchy stress vector established in Appendix B as a consequence of the balance of angular momentum. In Section V, the thermodynamic analysis of Appendix C is generalized to obtain appropriate expressions for the power expenditure and the energy, heat, and entropy transfers that accompany the evaporation-condensation and concomitant crystallization of the thin film at constant temperature. The first and second laws are discussed in Section VI. In Section VII, the energy balance and entropy imbalance are combined to yield an energy imbalance for isothermal processes which, when localized, furnishes dissipation inequalities away and at the phase boundary. These inequalities serve as guidelines for the imposition of thermodynamically consistent constitutive relations. In particular, the driving force behind spherulitic crystallization is identified as the conjugate of the migrational velocity of the phase boundary in the interfacial dissipation inequality and a kinetic relation that relates it to the growth rate is proposed. In Sections VIII and IX, we specialize the theory to experimentally relevant situations in which both species that make up the thin-film blend are involatile, and the adherence boundary condition applies at the vapor-solid interface. Section X contains two further specializations to binary films with a major species (the solute) and a minor one (the additive). The first considers growth kinetics when the solute and additive are in solution inside of the spherulite, whereas the second pertains to situations in which solute and additive molecules become segregated in the spherulitic phase. Section XI concludes with some remarks and comparisons with existing experimental data.

II. KINEMATICS

We consider a ternary thin-film blend composed of two solutes, $\mathcal{A}$ and $\mathcal{B}$, and a solvent $\mathcal{S}$. The generalization to an arbitrary number of chemical species is straightforward. When the film is exposed to a vapor of its constituents and a carrier gas, each constituent undergoes evaporation or condensation. However, from Section VIII onward, we will restrict our attention to situations in which the solutes $\mathcal{A}$ and $\mathcal{B}$ are involatile. In Section X, we will further specialize to films in which the mole fraction of solute $\mathcal{B}$ is small and the solvent $\mathcal{S}$ is present only in minuscule amounts. Under this scenario, $\mathcal{B}$ is referred to as the additive. Throughout, the vapor is assumed to be a mixture of ideal gases.

We assume that the film consists at all times of a crystalline phase and an amorphous phase, where by amorphous we also mean a phase of “limited ordering” [16]. At each time t , the crystalline phase occupies a bounded, simply connected domain $\Omega^s(t)$ in the plane, while the amorphous phase occupies the region $\Omega^a(t)$, which can be either bounded or unbounded. We denote by $\Gamma(t) = \partial\Omega^a(t) \cap \partial\Omega^s(t)$ the interface separating amorphous and crystalline phases.

We assume that Γ is smoothly evolving and write $\mathbf{n}$ for its unit normal pointing into the amorphous region Ω^a and V for its normal velocity. Let $\mathbf{t}$ be the unit tangent to Γ , chosen such that the crystalline phase Ω^s falls to its right. The (signed) curvature κ of the interface, a planar curve, is given by the Frenet relation (see, e.g., [29])

$$\frac{\partial \mathbf{t}}{\partial s} = \kappa \mathbf{n}, \quad (1)$$

where s denotes the arc length along Γ . Note that under this definition and our choice of $\mathbf{t}$ and $\mathbf{n}$, $\kappa \leq 0$ on Γ whenever Ω^s is convex.

In the absence of slip at the interface between the crystalline and amorphous regions, the material velocity $\mathbf{v}$ of the film is continuous across Γ . It follows that the migrational velocity

$$V^{\text{mig}} = V - \mathbf{v} \cdot \mathbf{n} \quad (2)$$

of the phase boundary relative to the thin-film material is well defined.

Next, consider a time-dependent domain $\mathcal{R}(t)$ that intersects the phase boundary $\Gamma(t)$ along the subcurve $\Sigma(t)$, and denote by $\mathbf{x}_0$ and $\mathbf{x}_1$ the endpoints of Σ (i.e., the points at which the boundary $\partial\mathcal{R}$ intersects Γ), chosen consistently with the clockwise orientation of Γ . Let $\mathbf{n}_{\partial\mathcal{R}}$ be the outer unit normal to $\partial\mathcal{R}$ and denote by $V_{\partial\mathcal{R}}^\perp$ its normal velocity. We write

$$V_{\partial\mathcal{R}}^{\text{mig}} = V_{\partial\mathcal{R}}^\perp - \mathbf{v} \cdot \mathbf{n}_{\partial\mathcal{R}} \quad (3)$$

for the migrational velocity of $\partial\mathcal{R}$.

Letting ϱ_i^α be the mass density of the i th species in the α phase (hereafter $\alpha = a, s$ and $i = \mathcal{A}, \mathcal{B}, \mathcal{S}$), we denote

by

$$\varrho^\alpha = \sum_{i=\mathcal{A}, \mathcal{B}, \mathcal{S}} \varrho_i^\alpha \quad (4)$$

the total mass density in the α phase. Similarly, we write F_i^α for the flux of molecules of the i th species from the vapor into the α phase and let

$$F^\alpha = \sum_{i=\mathcal{A}, \mathcal{B}, \mathcal{S}} F_i^\alpha \quad (5)$$

be the corresponding net mass flux. Hence, $F_i^\alpha > 0$ ($F_i^\alpha < 0$) whenever molecules of the i th species condense on (evaporate from) the α phase.

Let φ ($\boldsymbol{\varphi}$) be any scalar (vector) field defined in both phases and denote by φ^a ($\boldsymbol{\varphi}^a$) and φ^s ($\boldsymbol{\varphi}^s$) its restrictions to the amorphous and spherulitic phases, respectively. Let $\dot{\varphi}$ ($\dot{\boldsymbol{\varphi}}$) be the material time derivative of φ ($\boldsymbol{\varphi}$). By the chain rule,

$$\begin{cases} \dot{\varphi} = \frac{\partial \varphi}{\partial t} + \mathbf{v} \cdot \nabla \varphi, \\ \dot{\boldsymbol{\varphi}} = \frac{\partial \boldsymbol{\varphi}}{\partial t} + (\nabla \boldsymbol{\varphi}) \mathbf{v}. \end{cases} \quad (6)$$

Assuming that φ ($\boldsymbol{\varphi}$) is smooth up to the interface, we write φ_+^a ($\boldsymbol{\varphi}_+^a$) and φ_-^s ($\boldsymbol{\varphi}_-^s$) for the limiting values of φ ($\boldsymbol{\varphi}$) as the interface is approached from the amorphous and crystalline regions, respectively. The jump $[[\varphi]]$ across the interface is defined by

$$[[\varphi]] = \varphi_+^a - \varphi_-^s. \quad (7)$$

(An identical definition for the jump of $\boldsymbol{\varphi}$ holds at the interface.)

For any such scalar field φ , we have the following transport identity

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \varrho \varphi \, da &= \int_{\mathcal{R}} (\varrho \dot{\varphi} + \varphi F) \, da \\ &\quad - \int_{\Sigma} [[\varrho \varphi]] V^{\text{mig}} \, ds + \int_{\partial\mathcal{R}} \varrho \varphi V_{\partial\mathcal{R}}^{\text{mig}} \, ds, \end{aligned} \quad (8)$$

where V^{mig} , $V_{\partial\mathcal{R}}^{\text{mig}}$, ϱ , and F are given by (2)–(5) and the superscript α is omitted when notational convenience demands it, e.g.,

$$\int_{\mathcal{R}} \varphi \, da = \int_{\mathcal{R} \cap \Omega^a} \varphi^a \, da + \int_{\mathcal{R} \cap \Omega^s} \varphi^s \, da. \quad (9)$$

Let $\phi = \varphi/\varrho$. Substituting $\dot{\varphi} = \dot{\phi}/\varrho - \phi \dot{\varrho}/\varrho^2$ in (8), we obtain

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \phi \, da &= \int_{\mathcal{R}} \left(\dot{\phi} + \frac{\phi}{\varrho} (F - \dot{\varrho}) \right) \, da \\ &\quad - \int_{\Sigma} [[\phi]] V^{\text{mig}} \, ds + \int_{\partial\mathcal{R}} \phi V_{\partial\mathcal{R}}^{\text{mig}} \, ds. \end{aligned} \quad (10)$$

Analogous transport relations hold for any vector field $\boldsymbol{\varphi}$ smooth up to the interface.

Finally, we have the following interfacial transport identity

$$\frac{d}{dt} \int_{\Sigma} ds = \int_{\Sigma} \left(\frac{\partial \mathbf{v}}{\partial s} \cdot \mathbf{t} - \kappa V^{\text{mig}} \right) ds + \int_{\partial \Sigma} \mathbf{v}_{\partial \Sigma}^{\text{mig}} \cdot \mathbf{t}, \quad (11)$$

where, letting $\mathbf{v}_1$ ($\mathbf{v}_0$) and $\mathbf{t}_1$ ($\mathbf{t}_0$) denote the material velocity and interfacial unit tangent at the endpoint $\mathbf{x}_1$ ($\mathbf{x}_0$), we use the notation

$$\int_{\partial \Sigma} \mathbf{v}_{\partial \Sigma}^{\text{mig}} \cdot \mathbf{t} = (\dot{\mathbf{x}}_1 - \mathbf{v}_1) \cdot \mathbf{t}_1 - (\dot{\mathbf{x}}_0 - \mathbf{v}_0) \cdot \mathbf{t}_0. \quad (12)$$

The transport relations (8) and (11) are derived in Appendix A.

III. MASS BALANCES

Let $\mathbf{f}_i$ be the flux of molecules of the i th species from the vapor to the phase boundary. Thus, $\mathbf{f}_i > 0$ ($\mathbf{f}_i < 0$) during condensation (evaporation) of the i th species at the phase boundary. Mass balance requires that, for each species and for any migrating region $\mathcal{R}$,

$$\frac{d}{dt} \int_{\mathcal{R}} \varrho_i da - \int_{\partial \mathcal{R}} \varrho_i V_{\partial \mathcal{R}}^{\text{mig}} ds = \int_{\mathcal{R}} F_i da + \int_{\Sigma} \mathbf{f}_i ds, \quad (13)$$

In view of (2), (3), and (6)₁, and on appeal to the standard transport theorem (cf. (A.1) in Appendix A) and the divergence theorem, localization of (13) yields the balances

$$\dot{\varrho}_i^\alpha + \varrho_i^\alpha \nabla \cdot \mathbf{v} = F_i^\alpha \quad (14)$$

in each of the amorphous and crystalline regions, Ω^α and Ω^s , and the jump conditions

$$-[[\varrho_i]] V^{\text{mig}} = \mathbf{f}_i \quad (15)$$

at the phase boundary Γ separating them.

Summing (14) and (15) over all three species, we obtain

$$\nabla \cdot \mathbf{v} = \frac{1}{\varrho^\alpha} (F^\alpha - \dot{\varrho}^\alpha) \quad (16)$$

in each of the amorphous and crystalline phases, with ϱ^α given by (4) and F^α by (5), and

$$-[[\varrho]] V^{\text{mig}} = \mathbf{f} \quad (17)$$

at the interface between them, where

$$\mathbf{f} = \sum_{i=A,B,S} \mathbf{f}_i \quad (18)$$

is the net molecular flux from the vapor to the phase boundary.

Finally, note that, in view of (6)₁, (16) can be rewritten as

$$\frac{\partial \varrho^\alpha}{\partial t} + \nabla \cdot (\varrho^\alpha \mathbf{v}) = F^\alpha. \quad (19)$$

IV. MOMENTUM BALANCE

Our objective is to develop a theory for solvent-vapor induced spherulitic growth in solution-processed binary films under isothermal conditions. During solution processing, the solutes $\mathcal{A}$ and $\mathcal{B}$ are dissolved in the solvent $\mathcal{S}$, after which the solution is spin coated on a substrate to form a thin film. There will usually be residual solvent left in the spin-coated film. In the experiments of Lloyd *et al.* [7], the residual solvent is used for the subsequent solvent-vapor annealing. Alternatively, in the works of Lee *et al.* [8] and Lee *et al.* [16], the spin-coated film is thermally annealed to drive off the remaining solvent before it is exposed to the vapor of another solvent for vapor annealing.

In the first instance, where the film does not undergo thermal annealing, the procedures of solution processing and the likely presence of solvent at the film-substrate interface suggest that, prior to spherulitic crystallization, the initial stress in the film is spherical and the film is in smooth contact with the substrate throughout the process of spherulitic growth. For the case where thermal annealing is a processing step, upon vapor annealing solvent molecules will get into the thin film. It seems physically plausible that the same assertions on initial stress and on the condition of smooth contact would remain valid. In what follows we will adopt these assertions as physical assumptions. Moreover we will assume that both the amorphous and crystalline phases of the solid film are mechanically isotropic at the macroscopic scale.

Let $\mathbf{T}$ be the Cauchy stress tensor of the substrate, p^v be the vapor pressure, and

$$\boldsymbol{\sigma} = \sigma \mathbf{t} \quad (20)$$

be the interfacial Cauchy stress vector of the phase boundary. That $\boldsymbol{\sigma}$ remains tangential follows from the angular momentum balance (see Appendix B). The assumption of smooth contact between the film and the substrate entails the condition that the reactive force $\mathbf{T}\mathbf{e}$ be parallel to the unit normal $\mathbf{e}$ to the substrate pointing into the vapor phase, viz.,

$$\mathbf{T}\mathbf{e} = \tau \mathbf{e}. \quad (21)$$

Based on the physical assumptions above, the effects of shear stresses can be ignored and the Cauchy stress tensor $\mathbf{T}$ in the film can be taken as spherical,

$$\mathbf{T}^\alpha = -p^\alpha \mathbf{P} \quad (22)$$

in each of the amorphous and spherulitic regions, where $\mathbf{P} = \mathbf{1} - \mathbf{e} \otimes \mathbf{e}$ is the projection onto the plane of the substrate.

Next, denote by $\mathbf{v}^v$ the velocity of the vapor flow and let $\mathbf{u}_i$ be the (macroscopic) velocity of those molecules of the i th species that are condensing on or evaporating from the film. Hence,

$$\mathbf{u}_i = \begin{cases} \mathbf{v} & \text{during evaporation,} \\ \mathbf{v}^v & \text{during condensation} \end{cases} \quad (23)$$

of the i th species.

Momentum balance requires that, for each migrating region $\mathcal{R}$,

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \varrho \mathbf{v} da - \int_{\partial \mathcal{R}} \varrho \mathbf{v} V_{\partial \mathcal{R}}^{\text{mig}} ds = \\ - \int_{\partial \mathcal{R}} p \mathbf{n}_{\partial \mathcal{R}} ds + \int_{\mathcal{R}} \mathbb{T} \mathbf{e} da - \int_{\mathcal{R}} p^v \mathbf{e} da + \int_{\partial \Sigma} \boldsymbol{\sigma} \\ + \int_{\mathcal{R}} \mathbf{u}_i F_i da + \int_{\Sigma} \mathbf{u}_i \mathbf{f}_i ds, \end{aligned} \quad (24)$$

where summation over the repeated index i is implied and, letting $\boldsymbol{\sigma}_1 = \boldsymbol{\sigma}(\mathbf{x}_1, t)$ and $\boldsymbol{\sigma}_0 = \boldsymbol{\sigma}(\mathbf{x}_0, t)$, we use the notation

$$\int_{\partial \Sigma} \boldsymbol{\sigma} = \boldsymbol{\sigma}_1 - \boldsymbol{\sigma}_0. \quad (25)$$

The second term on the left-hand side of (24) accounts, modulo sign, for the flow of momentum through the boundary as a result of its migration relative to the film. The last two integrals on the right-hand side of (24) represent the flow of momentum associated with evaporation-condensation away and at the phase boundary.

In view of (5), (8), (21) and the divergence theorem, localization of (24) yields the pointwise balance

$$-\nabla p^\alpha + \sum_{i=A,B,S} (\mathbf{u}_i - \mathbf{v}) F_i^\alpha + (\tau - p^v) \mathbf{e} = \varrho^\alpha \dot{\mathbf{v}} \quad (26)$$

in each of the amorphous and crystalline phases.

In this paper we are interested only in physical settings under which the motion of the film can be taken as planar ($\mathbf{v} \cdot \mathbf{e} = 0$). Hence we have $\dot{\mathbf{v}} \cdot \mathbf{e} = 0$. As a result, when projected on the direction perpendicular to the substrate, (26) yields the relation

$$\tau = p^v - \sum_{i=A,B,S} (\mathbf{u}_i \cdot \mathbf{e}) F_i^\alpha. \quad (27)$$

In particular, when all three species are evaporating or in the event that they are condensing from a vapor stream that is parallel to the planar film ($\mathbf{v}^v \cdot \mathbf{e} = 0$), (27) reduces by (23) to the balance

$$\tau = p^v \quad (28)$$

between the vapor pressure and the reactive force exerted by the substrate on the film.

At the interface, using (8), (17), (18), and the fundamental theorem for line integrals, localization of (24) yields the interfacial momentum balance

$$-[[p]] \mathbf{n} + \frac{\partial \boldsymbol{\sigma}}{\partial s} = \sum_{i=A,B,S} (\mathbf{v} - \mathbf{u}_i) \mathbf{f}_i. \quad (29)$$

Since $\boldsymbol{\sigma}$ is tangential to the interface, we appeal to the Frenet relation (1) to conclude that the normal component of (29) takes the form

$$-[[p]] + \sigma \kappa = \sum_{i=A,B,S} (\mathbf{v} - \mathbf{u}_i) \cdot \mathbf{n} \mathbf{f}_i. \quad (30)$$

Note that, by (23)₁, evaporating species do not contribute to the right-hand side of (30). Similarly, by (23)₂, species that condense from a vapor flow satisfying the adherence boundary condition at the film-vapor interface ($\mathbf{v}^v = \mathbf{v}$) do not contribute to the right-hand side of (30). In this case, (30) reduces to the classical Young-Laplace equation

$$-[[p]] + \sigma \kappa = 0. \quad (31)$$

V. POWER EXPENDITURE; ENERGY, HEAT, AND ENTROPY FLOWS

Consider a thermodynamic system $\mathcal{R}(t)$ consisting of the union of the part of the film defined by $\mathcal{R}(t)$ and the molecules in the vapor phase which, at time t , are condensing on or evaporating from $\mathcal{R}(t)$.

A. Power expenditures

Let p_i^v denote the partial pressure of the i th species in the vapor. The net power expended by the forces acting on $\mathcal{R}(t)$ can be written as

$$\begin{aligned} \mathcal{P}(\mathcal{R}) = - \int_{\partial \mathcal{R}} p \mathbf{n}_{\partial \mathcal{R}} \cdot \mathbf{v} ds + \int_{\partial \Sigma} \boldsymbol{\sigma} \cdot \mathbf{v} \\ + \sum_{i=A,B,S} \left(\int_{\mathcal{R}} \frac{p_i^v}{\varrho_i^v} F_i da + \int_{\Sigma} \frac{p_i^v}{\varrho_i^v} \mathbf{f}_i ds \right), \end{aligned} \quad (32)$$

where, recalling that $\boldsymbol{\sigma}_1$ ($\boldsymbol{\sigma}_0$) is the interfacial stress at the endpoint $\mathbf{x}_1$ ($\mathbf{x}_0$) of Σ and $\mathbf{v}_1$ ($\mathbf{v}_0$) is its material velocity,

$$\int_{\partial \Sigma} \boldsymbol{\sigma} \cdot \mathbf{v} = \boldsymbol{\sigma}_1 \cdot \mathbf{v}_1 - \boldsymbol{\sigma}_0 \cdot \mathbf{v}_0. \quad (33)$$

The first two integrals on the right-hand side of (32) account for the power expenditures associated with the pressure in the film and the line tension along the interface. The remaining terms represent the power expended by the partial pressures of the evaporating or condensing species in the vapor (see Appendix C). Note that, as a consequence of (21) and the planar motion of the film, the power expenditure associated with the reactive force exerted by the substrate on the film vanishes, viz.,

$$\int_{\mathcal{R}} \mathbb{T} \mathbf{e} \cdot \mathbf{v} da = 0. \quad (34)$$

In view of (16) and the divergence theorem,

$$\begin{aligned} - \int_{\partial\mathcal{R}} p \mathbf{n}_{\partial\mathcal{R}} \cdot \mathbf{v} \, ds &= - \int_{\mathcal{R}} \nabla p \cdot \mathbf{v} \, da \\ &\quad - \int_{\mathcal{R}} \frac{p}{\varrho} (F - \dot{\varrho}) \, da - \int_{\Sigma} \llbracket p \rrbracket \mathbf{n} \cdot \mathbf{v} \, ds. \end{aligned} \quad (35)$$

Moreover, by (20) and the fundamental theorem for line integrals,

$$\int_{\partial\Sigma} \boldsymbol{\sigma} \cdot \mathbf{v} = \int_{\Sigma} \left(\varrho \frac{\partial \boldsymbol{\sigma}}{\partial s} \cdot \mathbf{v} + \boldsymbol{\sigma} \mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s} \right) ds. \quad (36)$$

Hence, substituting (35) and (36) in (32) and invoking the momentum balances (26) and (29), we obtain

$$\begin{aligned} \mathcal{P}(\mathcal{R}) &= \int_{\mathcal{R}} \left(\varrho \mathbf{v} \cdot \dot{\mathbf{v}} - \sum_{i=A,B,S} \mathbf{v} \cdot (\mathbf{u}_i - \mathbf{v}) F_i \right) da \\ &\quad - \int_{\mathcal{R}} \frac{p}{\varrho} (F - \dot{\varrho}) \, da - \sum_{i=A,B,S} \int_{\Sigma} \mathbf{v} \cdot (\mathbf{u}_i - \mathbf{v}) \mathbf{f}_i \, ds + \int_{\Sigma} \boldsymbol{\sigma} \mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s} \, ds \\ &\quad + \sum_{i=A,B,S} \left(\int_{\mathcal{R}} \frac{p_i^v}{\varrho_i^v} F_i \, da + \int_{\Sigma} \frac{p_i^v}{\varrho_i^v} \mathbf{f}_i \, ds \right). \end{aligned} \quad (37)$$

B. Energy and entropy flows; heating

Let ε_i^v denote the specific internal energy of the i th species in the vapor. In view of Appendix C, we express the flow $\mathcal{F}(\mathcal{R})$ of internal and kinetic energies that results from condensation on or evaporation from $\mathcal{R}(t)$ in the form

$$\begin{aligned} \mathcal{F}(\mathcal{R}) &= \int_{\mathcal{R}} \varepsilon_i^v F_i \, da + \int_{\Sigma} \varepsilon_i^v \mathbf{f}_i \, ds \\ &\quad + \frac{1}{2} \int_{\mathcal{R}} |\mathbf{u}_i|^2 F_i \, da + \frac{1}{2} \int_{\Sigma} |\mathbf{u}_i|^2 \mathbf{f}_i \, ds, \end{aligned} \quad (38)$$

where summation over the repeated index i is implied, e.g.,

$$\begin{aligned} \int_{\mathcal{R}} \varepsilon_i^v F_i \, da &= \sum_{i=A,B,S} \left(\int_{\mathcal{R} \cap \Omega^a} \varepsilon_i^v F_i^a \, da \right. \\ &\quad \left. + \int_{\mathcal{R} \cap \Omega^s} \varepsilon_i^v F_i^s \, da \right). \end{aligned} \quad (39)$$

The first two terms on the right-hand side of (38) represent the flow of internal energy that accompanies evaporation or condensation. The remaining two terms account for the corresponding flow of kinetic energy.

Further, let η_i^v denote the specific entropy of the i th species in the vapor. The rate at which entropy is transferred into or out of $\mathcal{R}(t)$ during evaporation or condensation is given by

$$\mathcal{H}(\mathcal{R}) = \int_{\mathcal{R}} \eta_i^v F_i \, da + \int_{\Sigma} \eta_i^v \mathbf{f}_i \, ds. \quad (40)$$

As with (32), the form of (40) follows from the thermodynamic arguments of Appendix C.

Finally, denoting by r^α the areal density of heat supply that accompanies evaporation from or condensation on the α phase and by $\mathbf{r}$ its lineal counterpart at the interface, we write

$$\mathcal{Q}(\mathcal{R}) = \int_{\mathcal{R}} r \, da + \int_{\Sigma} \mathbf{r} \, ds \quad (41)$$

for the rate at which heat is exchanged between the system $\mathcal{R}$ and its environment in order to keep the temperature constant.

VI. FIRST AND SECOND LAWS; ENERGY IMBALANCE

Let ε^α be the areal internal-energy density of the α phase and ϵ be its lineal counterpart for the phase boundary between the amorphous and crystalline regions. The net (internal + kinetic) energy associated with the migrating region $\mathcal{R}$ is defined by

$$\mathcal{E}(\mathcal{R}) = \int_{\mathcal{R}} \left(\varepsilon + \frac{1}{2} \varrho |\mathbf{v}|^2 \right) da + \int_{\Sigma} \epsilon \, ds, \quad (42)$$

where, since it is massless, no kinetic energy is associated with the phase boundary.

Similarly, denote by η^α the entropy per unit area of the α phase and by ς the lineal density of entropy associated with the phase boundary. The net entropy of $\mathcal{R}$ is given by

$$S(\mathcal{R}) = \int_{\mathcal{R}} \eta \, da + \int_{\Sigma} \varsigma \, ds. \quad (43)$$

A. Energy balance

In light of the thermodynamic analysis of Appendix C, the first law states that the rate at which the net energy of the migrating region $\mathcal{R}(t)$ changes is balanced by the sum of (i) the power expended by external agencies on the system $\mathcal{R}(t)$ consisting, at each time t , of $\mathcal{R}(t)$ and the molecules condensing on or evaporating from it at the time in question, (ii) the energy flow into or out of $\mathcal{R}(t)$, (iii) the heating into or out of $\mathcal{R}$ to keep the temperature

constant, and (iv) the energy flow that accompanies the migration of the boundary $\partial\mathcal{R}(t)$. Specifically,

$$\begin{aligned} \frac{d\mathcal{E}(\mathcal{R})}{dt} = & \mathcal{P}(\mathcal{R}) + \mathcal{F}(\mathcal{R}) + \mathcal{Q}(\mathcal{R}) \\ & + \int_{\partial\mathcal{R}} \left(\varepsilon + \frac{1}{2} \varrho |\mathbf{v}|^2 \right) V_{\partial\mathcal{R}}^{\text{mig}} ds + \int_{\partial\Sigma} \epsilon \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t}, \end{aligned} \quad (44)$$

where, letting ϵ_1 (ϵ_0) denote the internal energy per unit length of the interface evaluated at the endpoint $\mathbf{x}_1$ ($\mathbf{x}_0$) of Σ , we use the notation

$$\int_{\partial\Sigma} \epsilon \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t} = \epsilon_1(\dot{\mathbf{x}}_1 - \mathbf{v}_1) \cdot \mathbf{t}_1 - \epsilon_0(\dot{\mathbf{x}}_0 - \mathbf{v}_0) \cdot \mathbf{t}_0. \quad (45)$$

In (44), the power expenditure $\mathcal{P}(\mathcal{R})$, the energy flow $\mathcal{F}(\mathcal{R})$, and the heating $\mathcal{Q}(\mathcal{R})$ are given by (37), (38), and (41), respectively. The integral before last on the right-hand side of (44) accounts for the transfer of internal and kinetic energies across the boundary $\partial\mathcal{R}$ as a result of its motion, while the last integral represents the flow of interfacial internal energy as the endpoints of Σ migrate along the evolving phase boundary.

B. Entropy imbalance

The second law takes the form of an entropy imbalance asserting that the rate at which the net entropy $S(\mathcal{R})$ changes be at least as great as the rate at which entropy flows into or out of $\mathcal{R}(t)$ as a result of evaporation-condensation and the migration of its boundary, augmented by terms that account for the transfer of heat between the system $\mathcal{R}(t)$ and its environment.

Letting Θ denote the absolute temperature, we therefore have

$$\begin{aligned} \frac{dS(\mathcal{R})}{dt} \geq & \mathcal{H}(\mathcal{R}) + \int_{\mathcal{R}} \frac{r}{\Theta} da + \int_{\Sigma} \frac{\mathbf{r}}{\Theta} ds \\ & + \int_{\partial\mathcal{R}} \eta V_{\partial\mathcal{R}}^{\text{mig}} ds + \int_{\partial\Sigma} \varsigma \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t}, \end{aligned} \quad (46)$$

where $\mathcal{H}(\mathcal{R})$ is given by (40). As with (44), the integral before last on the right-hand side of (46) represents the flow of entropy that accompanies the migration of $\partial\mathcal{R}$ in the plane of the substrate and the last integral,

$$\int_{\partial\Sigma} \varsigma \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t} = \varsigma_1(\dot{\mathbf{x}}_1 - \mathbf{v}_1) \cdot \mathbf{t}_1 - \varsigma_0(\dot{\mathbf{x}}_0 - \mathbf{v}_0) \cdot \mathbf{t}_0, \quad (47)$$

where ς_1 (ς_0) denotes the lineal density of interfacial entropy at the endpoint $\mathbf{x}_1$ ($\mathbf{x}_0$) of Σ , embodies the entropy flow associated with the motion of $\mathbf{x}_1$ and $\mathbf{x}_0$ along the phase boundary.

C. Energy imbalance

Since evaporation-condensation is assumed to occur under isothermal conditions, (46) can be rewritten as

$$\begin{aligned} -\frac{d(\Theta S(\mathcal{R}))}{dt} \leq & -\mathcal{Q}(\mathcal{R}) - \int_{\mathcal{R}} \Theta \eta_i^v F_i da - \int_{\Sigma} \Theta \eta_i^v \mathbf{f}_i ds \\ & - \int_{\partial\mathcal{R}} \Theta \eta V_{\partial\mathcal{R}}^{\text{mig}} ds - \int_{\partial\Sigma} \Theta \varsigma \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t}. \end{aligned} \quad (48)$$

Combining (44) and (48) yields the (free + kinetic) energy imbalance

$$\begin{aligned} \frac{d}{dt} \left(\int_{\mathcal{R}} \left(\Psi + \frac{1}{2} \varrho |\mathbf{v}|^2 \right) da + \int_{\Sigma} \psi ds \right) \leq \\ \int_{\partial\mathcal{R}} \left(\Psi + \frac{1}{2} \varrho |\mathbf{v}|^2 \right) V_{\partial\mathcal{R}}^{\text{mig}} ds + \int_{\partial\Sigma} \psi \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t} + \mathcal{P}(\mathcal{R}) \\ + \mathcal{F}(\mathcal{R}) - \int_{\mathcal{R}} \Theta \eta_i^v F_i da - \int_{\Sigma} \Theta \eta_i^v \mathbf{f}_i ds, \end{aligned} \quad (49)$$

where the power expenditure $\mathcal{P}(\mathcal{R})$ and energy flow $\mathcal{F}(\mathcal{R})$ are given by (37) and (38),

$$\Psi^\alpha = \varepsilon^\alpha - \Theta \eta^\alpha \quad (50)$$

is the areal free-energy density of the α phase, and

$$\psi = \epsilon - \Theta \varsigma \quad (51)$$

is the free energy per unit length of the phase boundary. The first integral on the right-hand side of (49) represents the flow of free and kinetic energies that accompanies the migration of $\partial\mathcal{R}$. The second integral,

$$\int_{\partial\Sigma} \psi \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t} = \psi_1(\dot{\mathbf{x}}_1 - \mathbf{v}_1) \cdot \mathbf{t}_1 - \psi_0(\dot{\mathbf{x}}_0 - \mathbf{v}_0) \cdot \mathbf{t}_0, \quad (52)$$

where ψ_1 (ψ_0) denotes the lineal density of interfacial free energy at the endpoint $\mathbf{x}_1$ ($\mathbf{x}_0$), accounts for the flow of interfacial free energy that results from the motion of the endpoints of Σ along the phase boundary.

VII. DISSIPATION INEQUALITIES AND CONSTITUTIVE THEORY

A. Bulk dissipation inequality and constitutive relations

In view of (5), (10), (37), and (38), localization of the energy imbalance (49) yields the dissipation inequality

$$\begin{aligned} \dot{\Psi}^\alpha + \frac{1}{\varrho^\alpha} (\Psi^\alpha + p^\alpha) (F^\alpha - \dot{\varrho}^\alpha) \\ - \mu_i^v F_i^\alpha - \frac{1}{2} \sum_{i=A,B,S} |\mathbf{v} - \mathbf{u}_i|^2 F_i^\alpha \leq 0 \end{aligned} \quad (53)$$

in each of the amorphous and crystalline phases, where

$$\mu_i^v = \varepsilon_i^v - \Theta \eta_i^v + \frac{p_i^v}{\varrho_i^v} \quad (54)$$

is the chemical potential of the i th species in the vapor.

Let

$$\vec{\varrho}^\alpha = (\varrho_A^\alpha, \varrho_B^\alpha, \varrho_S^\alpha) \quad (55)$$

and consider the constitutive relation

$$\Psi^\alpha = \Psi^\alpha(\Theta, \vec{\varrho}^\alpha) \quad (56)$$

giving the free-energy density of the α phase when the temperature and the densities of the chemical constituents of the phase under consideration are known. Since we restrict our attention to solvent-vapor induced spherulitic crystallization under isothermal conditions, we hereafter suppress the explicit dependence on Θ in all constitutive functions that have the temperature as a canonical independent variable. Hence, (56) is replaced by

$$\Psi^\alpha = \Psi^\alpha(\vec{\varrho}^\alpha). \quad (57)$$

Appealing to (14) and (16), one can show that

$$\dot{\Psi}^\alpha = \mu_i^\alpha \left(F_i^\alpha - \frac{\varrho_i^\alpha}{\varrho^\alpha} (F^\alpha - \dot{\varrho}^\alpha) \right), \quad (58)$$

where the chemical potential μ_i^α of the i th species in the α phase is given by the standard relation

$$\mu_i^\alpha = \frac{\partial \Psi^\alpha}{\partial \varrho_i^\alpha}. \quad (59)$$

Next, let

$$\omega^\alpha = \Psi^\alpha - \mu_i^\alpha \varrho_i^\alpha \quad (60)$$

denote the grand canonical potential of the α phase. Substitution of (58) in (53) then yields the inequality

$$\begin{aligned} (\mu_i^\alpha - \mu_i^v) F_i^\alpha - \frac{1}{2} \sum_{i=A,B,S} |\mathbf{v} - \mathbf{u}_i|^2 F_i^\alpha \\ + \frac{1}{\varrho^\alpha} (\omega^\alpha + p^\alpha) (F^\alpha - \dot{\varrho}^\alpha) \leq 0 \end{aligned} \quad (61)$$

in each phase. In view of the well-known thermodynamic relation [30]

$$-p^\alpha = \omega^\alpha, \quad (62)$$

the dissipation inequality (61) trivially delivers the reduced dissipation inequality

$$(\mu_i^\alpha - \mu_i^v) F_i^\alpha - \frac{1}{2} \sum_{i=A,B,S} |\mathbf{v} - \mathbf{u}_i|^2 F_i^\alpha \leq 0. \quad (63)$$

Whenever the i th species is evaporating, $\mathbf{u}_i = \mathbf{v}$. Its contribution to the second term on the left-hand side of

(61) therefore vanishes identically. If on the other hand the i th species is condensing, $\mathbf{u}_i = \mathbf{v}^v$. Since $F_i^\alpha > 0$ during condensation, the contribution of the i th species to the term in question is always nonpositive. Hence, in all cases,

$$\sum_{i=A,B,S} |\mathbf{v} - \mathbf{u}_i|^2 F_i^\alpha \geq 0. \quad (64)$$

It follows that the constitutive relations

$$F_i^\alpha = -K_i^\alpha (\mu_i^\alpha - \mu_i^v), \quad (65)$$

where $K_i^\alpha \geq 0$ and no summation over the repeated index i is implied, are sufficient to ensure that the dissipation inequality (61) is satisfied.

Note that for a pure substance, by (59) and (60), (62) reduces to

$$p^\alpha = -\Psi^\alpha + \varrho^\alpha \frac{\partial \Psi^\alpha}{\partial \varrho^\alpha}. \quad (66)$$

Let $\hat{\Psi}^\alpha = \Psi^\alpha / \varrho^\alpha$ denote the specific free energy of the α phase. Equation (66) then takes the form of the well-known pressure relation

$$p^\alpha = (\varrho^\alpha)^2 \frac{\partial \hat{\Psi}^\alpha}{\partial \varrho^\alpha}.$$

B. Interfacial dissipation inequality and constitutive relations

At the phase boundary, using the transport identities (10)–(11) and the expressions (37)–(38) for the power expended on $\mathcal{R}$ and the energy flow into or out of $\mathcal{R}$, we localize the energy imbalance (49) to yield

$$\begin{aligned} -[\Psi] V^{\text{mig}} - \frac{1}{2} [\varrho] |\mathbf{v}|^2 V^{\text{mig}} \\ + \psi \left(\frac{\partial \mathbf{v}}{\partial s} \cdot \mathbf{t} - \kappa V^{\text{mig}} \right) \leq \sigma \mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s} + \mu_i^v \mathbf{f}_i \\ - \sum_{i=A,B,S} \left(\mathbf{v} \cdot (\mathbf{u}_i - \mathbf{v}) - \frac{1}{2} |\mathbf{u}_i|^2 \right) \mathbf{f}_i, \end{aligned} \quad (67)$$

where the chemical potential μ_i^v of the i th species in the vapor is given by (54). In view of the interfacial mass balances (15) and (17), we have

$$-\frac{1}{2} [\varrho] |\mathbf{v}|^2 V^{\text{mig}} = \frac{1}{2} \sum_{i=A,B,S} |\mathbf{v}|^2 \mathbf{f}_i \quad (68)$$

and

$$\mu_i^v \mathbf{f}_i = -[\mu_i^v \varrho_i] V^{\text{mig}}. \quad (69)$$

Hence, substitution of (68) and (69) in (67) yields the interfacial dissipation inequality

$$\begin{aligned} -([\Psi] + \psi \kappa - [\mu_i^v \varrho_i]) V^{\text{mig}} \\ + (\psi - \sigma) \mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s} - \frac{1}{2} \sum_{i=A,B,S} |\mathbf{u}_i - \mathbf{v}|^2 \mathbf{f}_i \leq 0, \end{aligned} \quad (70)$$

which, on appealing to (60), can be rewritten as

$$-([\omega] + \psi\kappa + [(\mu_i - \mu_i^v)\varrho_i])V^{\text{mig}} + (\psi - \sigma)\mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s} - \frac{1}{2} \sum_{i=\mathcal{A}, \mathcal{B}, \mathcal{S}} |\mathbf{u}_i - \mathbf{v}|^2 \mathbf{f}_i \leq 0. \quad (71)$$

As with (61), the last term on the left hand side of (71) is nonpositive. Hence, the kinetic relation

$$[\omega] + \psi\kappa + [(\mu_i - \mu_i^v)\varrho_i] = \beta V^{\text{mig}}, \quad (72)$$

where $\beta \geq 0$ is referred to as the kinetic coefficient, and the constitutive relation

$$\sigma = \psi + \gamma \mathbf{t} \cdot \frac{\partial \mathbf{v}}{\partial s}, \quad (73)$$

with $\gamma \geq 0$ the interfacial viscosity, are sufficient for the interfacial dissipation inequality (71) to be satisfied. Note that, in view of (73), the interfacial line tension σ consists of an equilibrium contribution ψ and a dissipative contribution $\gamma \mathbf{t} \cdot \partial \mathbf{v} / \partial s$.

VIII. SPHERULITIC CRYSTALLIZATION UNDER SOLVENT-VAPOR ANNEALING

Hereafter we specialize the preceding theory to thin films formed by spin-coating a blend of two *involatile* species $\mathcal{A}$ and $\mathcal{B}$.

In the experiments reported in [8, 16, 28], the spin-coated films are thermally annealed to drive off the residual solvent. In each subsequent vapor-annealing experiment the thin film is put in a chamber and exposed to a uniform stream of filler gas plus the vapor of another solvent at low concentration, which flows parallel to the plane of the substrate. By controlling the concentration of solvent vapor in the flowing stream, the partial pressure p_s^v of the solvent vapor can be made different from one experiment to the other, although it is kept constant in each experiment. On the other hand, the total gas pressure p^v is always controlled to be constant and at the same fixed value for each set of experiments. The filler gas serves the purpose of carrying the vapor into the sample chamber while maintaining the total pressure of the gas mixture at fixed value. It otherwise plays no role in the physics of these experiments.

Let w_s be the molecular weight of the solvent. Under the assumption that the solvent vapor in the flowing stream is an ideal gas, its chemical potential is given by the formula

$$\mu_s^v(p_s^v) = \mu_0^v + w_s^{-1} R \Theta \ln p_s^v, \quad (74)$$

where R is the gas constant and the explicit dependence of μ_s^v and μ_0^v on temperature is suppressed. Formula (74) indicates that for a given temperature Θ the chemical potential μ_s^v of the solvent vapor is a strictly increasing function of its partial pressure p_s^v .

A. Role of solvent vapor

Prior to crystallization, the thermally annealed thin film is entirely amorphous. Since species $\mathcal{A}$ and $\mathcal{B}$ are involatile, $F_{\mathcal{A}}^a$ and $F_{\mathcal{B}}^a$ must vanish. Consequently, the mass balances (14) specialize to

$$\dot{\varrho}_i^a + \varrho_i^a \nabla \cdot \mathbf{v} = 0 \quad (i = \mathcal{A}, \mathcal{B}) \quad (75)$$

everywhere in the amorphous film. On the other hand, by (65) the constitutively augmented mass balance for the solvent takes the form

$$\dot{\varrho}_s^a + \varrho_s^a \nabla \cdot \mathbf{v} = -K_s^a(\mu_s^a - \mu_s^v), \quad (76)$$

where μ_s^v is prescribed by (74) and, recalling (59), the chemical potential of solvent molecules in the amorphous film is given by

$$\mu_s^a(\vec{\varrho}^a) = \frac{\partial \Psi^a(\vec{\varrho}^a)}{\partial \varrho_s^a}. \quad (77)$$

Next, appealing to (28) and (65), we see that the constitutively augmented momentum balance (26) reduces to

$$-\nabla p^a - K_s^a(\mathbf{u}_s - \mathbf{v})(\mu_s^a - \mu_s^v) = \varrho^a \dot{\mathbf{v}}, \quad (78)$$

where, in view of (57), (59), (60), and (62), the pressure in the amorphous film is constitutively determined by the densities of its constituents, viz.,

$$p^a(\vec{\varrho}^a) = -\Psi^a(\vec{\varrho}^a) + \varrho_i^a \mu_i^a(\vec{\varrho}^a). \quad (79)$$

Further, under isothermal conditions, the constitutively indeterminate density r^a of heat supply into or out of the amorphous film can be chosen such that the field equation that would result from the localization of the energy balance (44) is automatically satisfied.

Assuming that the thermally annealed, amorphous film is homogeneous, we denote by $\varrho_{\mathcal{A}}^*$ the initial (uniform) density of species $\mathcal{A}$ and by $\varrho_{\mathcal{B}}^*$ that of species $\mathcal{B}$. Since $\mu_s^a(\varrho_{\mathcal{A}}^*, \varrho_{\mathcal{B}}^*, 0) = -\infty$, when the thermally-annealed film is exposed to solvent vapor, solvent molecules will get into the amorphous film, as dictated by (65), until chemical equilibrium is reached between the solvent in the film and its gaseous counterpart in the flowing stream. At that point, we have

$$\mu_s^a(\varrho_{\mathcal{A}}^{\text{eq}}, \varrho_{\mathcal{B}}^{\text{eq}}, \varrho_s^{\text{eq}}) = \mu_s^v(p_s^v), \quad (80)$$

with $\varrho_{\mathcal{A}}^{\text{eq}}$, $\varrho_{\mathcal{B}}^{\text{eq}}$, and ϱ_s^{eq} the equilibrium densities of species $\mathcal{A}$, $\mathcal{B}$, and $\mathcal{S}$ in the amorphous film, respectively.

These densities can be determined as follows. From (75), we deduce that

$$\frac{\dot{\varrho}_{\mathcal{A}}^a}{\varrho_{\mathcal{A}}^a} = \frac{\dot{\varrho}_{\mathcal{B}}^a}{\varrho_{\mathcal{B}}^a}. \quad (81)$$

Next, integrating (81) with respect to time over the interval separating the beginning of vapor annealing from chemical equilibrium, we find

$$\frac{\varrho_{\mathcal{A}}^{\text{eq}}}{\varrho_{\mathcal{A}}^*} = \frac{\varrho_{\mathcal{B}}^{\text{eq}}}{\varrho_{\mathcal{B}}^*}. \quad (82)$$

Hence, there exists a scalar function J such that

$$\varrho_{\mathcal{A}}^{\text{eq}} = J\varrho_{\mathcal{A}}^* \quad \text{and} \quad \varrho_{\mathcal{B}}^{\text{eq}} = J\varrho_{\mathcal{B}}^*. \quad (83)$$

At the outer boundary of the amorphous phase, we assume that the no-slip condition holds for the flowing stream of vapor and filler gas and that line-tension effects are negligible. Mechanical equilibrium at the boundary in question then requires that

$$p^a(\varrho_{\mathcal{A}}^*, \varrho_{\mathcal{B}}^*, 0) \simeq p^v h \quad (84)$$

before exposure of the film to solvent vapor and

$$p^a(\varrho_{\mathcal{A}}^{\text{eq}}, \varrho_{\mathcal{B}}^{\text{eq}}, \varrho_{\mathcal{S}}^{\text{eq}}) \simeq p^v h \quad (85)$$

once chemical equilibrium with the vapor has been reached, where h is the thickness of the film at the outer boundary of the amorphous phase. Setting

$$\tilde{p}^a(J, \varrho_{\mathcal{S}}^{\text{eq}}) = p^a(J\varrho_{\mathcal{A}}^*, J\varrho_{\mathcal{B}}^*, \varrho_{\mathcal{S}}^{\text{eq}}), \quad (86)$$

it follows from (83), (84), and (85) that

$$\tilde{p}^a(1, 0) = \tilde{p}^a(J, \varrho_{\mathcal{S}}^{\text{eq}}) \simeq p^v h. \quad (87)$$

Assuming that

$$\frac{\partial \tilde{p}^a}{\partial \varrho_{\mathcal{S}}^{\text{eq}}}(1, 0) \neq 0, \quad (88)$$

we deduce from the implicit function theorem that there exists a function $\tilde{J}$ such that

$$J = \tilde{J}(\varrho_{\mathcal{S}}^{\text{eq}}, p^v) \quad \text{and} \quad \tilde{J}(0, p^v) = 1, \quad (89)$$

where $\tilde{J}$ is defined in a neighborhood of $(0, p^v)$ and has the same regularity of $\tilde{p}^a$.

In view of (83) and (89), the condition (80) for chemical equilibrium can now be rewritten as

$$\mu_{\mathcal{S}}^a(\tilde{J}(\varrho_{\mathcal{S}}^{\text{eq}}, p^v)\varrho_{\mathcal{A}}^*, \tilde{J}(\varrho_{\mathcal{S}}^{\text{eq}}, p^v)\varrho_{\mathcal{B}}^*, \varrho_{\mathcal{S}}^{\text{eq}}) = \mu_{\mathcal{S}}^v(p_{\mathcal{S}}^v), \quad (90)$$

with the chemical potential of the solvent vapor given by (74). The solution of this equation delivers the density $\varrho_{\mathcal{S}}^{\text{eq}}$ of solvent molecules in the film when it is in equilibrium with the vapor as a function of the temperature, the solvent-vapor pressure, and the initial composition of the amorphous film. The knowledge of this density leads, by means of (83) and (89), to the determination of $\varrho_{\mathcal{A}}^{\text{eq}}$ and $\varrho_{\mathcal{B}}^{\text{eq}}$.

Note that, in view of these equations,

$$\varrho_{\mathcal{S}}^{\text{eq}} \simeq 0 \quad \text{implies} \quad \varrho_{\mathcal{A}}^{\text{eq}} \simeq \varrho_{\mathcal{A}}^* \quad \text{and} \quad \varrho_{\mathcal{B}}^{\text{eq}} \simeq \varrho_{\mathcal{B}}^*. \quad (91)$$

Moreover, when $\varrho_{\mathcal{S}}^{\text{eq}}$ is small, equation (90) leads to Henry's law for dilute solutions

$$x_{\mathcal{S}}^{\text{eq}} \simeq K_H p_{\mathcal{S}}^v, \quad (92)$$

where $x_{\mathcal{S}}^{\text{eq}}$ is the mole fraction of the “dissolved” vapor $\mathcal{S}$ in the amorphous phase and, as it can be seen from (84),

(87) and (90), the coefficient K_H is a function of $\varrho_{\mathcal{A}}^*$, $\varrho_{\mathcal{B}}^*$, p^v , and the temperature Θ (which is suppressed in (90)). Later we shall see that when $\varrho_{\mathcal{S}}^{\text{eq}}$ is small, solvent vapor can affect the spherulitic growth rate V only through its effect on the kinetic coefficient β , which depends on the partial pressure $p_{\mathcal{S}}^v$ that determines the amount of solvent vapor dissolved in the amorphous film.

The role of solvent vapor in spherulitic crystallization of spin-coated amorphous films is illustrated clearly by the experiments of Lee *et al.* [16] on solvent-vapor annealing of single-component TES ADT films by DCE vapor. In those experiments it was observed that there was a threshold in the concentration of DCE vapor in the gas stream under which no spherulitic crystallization took place, and that spherulitic growth rate increased linearly with DCE vapor concentration above the threshold (see Fig. S3 in the Supporting Information of the aforementioned paper). When the gas stream can be taken as a flowing mixture of ideal gases, solvent-vapor concentration in the gas stream is directly proportional to the partial pressure $p_{\mathcal{S}}^v$, which in turn is directly proportional to the mole fraction $x_{\mathcal{S}}^v$ through (92). Hence the experimental finding of Lee *et al.* may be interpreted as follows: there is a threshold $x_{\mathcal{S}}^{\text{th}}$ in the mole fraction of “dissolved” vapor in the amorphous TES ADT film under which no spherulitic crystallization will occur; with all other conditions kept fixed, for $x_{\mathcal{S}}^{\text{eq}} \geq x_{\mathcal{S}}^{\text{th}}$, the growth rate of TES ADT spherulites is directly proportional to $x_{\mathcal{S}}^{\text{eq}} - x_{\mathcal{S}}^{\text{th}}$.

B. Spherulitic crystallization

After nucleation has occurred, the crystalline region is governed by equations that are identical to (75)–(79). Specifically, the mass balances for species $\mathcal{A}$ and $\mathcal{B}$ are given by

$$\dot{\varrho}_i^s + \varrho_i^s \nabla \cdot \mathbf{v} = 0 \quad (i = \mathcal{A}, \mathcal{B}) \quad (93)$$

everywhere inside the crystalline phase, while their counterpart for the solvent has the form

$$\dot{\varrho}_{\mathcal{S}}^s + \varrho_{\mathcal{S}}^s \nabla \cdot \mathbf{v} = -K_{\mathcal{S}}^s(\mu_{\mathcal{S}}^s - \mu_{\mathcal{S}}^v), \quad (94)$$

where the chemical potential of the solvent in the crystallite is defined by

$$\mu_{\mathcal{S}}^s(\vec{\varrho}^s) = \frac{\partial \Psi^s(\vec{\varrho}^s)}{\partial \varrho_{\mathcal{S}}^s}. \quad (95)$$

In view of (28) and (65), the momentum balance can be written as

$$-\nabla p^s - K_{\mathcal{S}}^s(\mathbf{u}_{\mathcal{S}} - \mathbf{v})(\mu_{\mathcal{S}}^s - \mu_{\mathcal{S}}^v) = \varrho^s \dot{\mathbf{v}}, \quad (96)$$

where, by (62),

$$p^s(\vec{\varrho}^s) = -\Psi^s(\vec{\varrho}^s) + \varrho_i^s \mu_i^s(\vec{\varrho}^s). \quad (97)$$

Since the amorphous phase is now saturated with solvent molecules, changes in $\vec{\varrho}^a$ can result only from the

deformation of the film itself. Assuming the deformation in the amorphous region to be negligible, we may take the densities of species $\mathcal{A}$, $\mathcal{B}$, and $\mathcal{S}$ in this region to be equal to their equilibrium values $\varrho_{\mathcal{A}}^{\text{eq}}$, $\varrho_{\mathcal{B}}^{\text{eq}}$, and $\varrho_{\mathcal{S}}^{\text{eq}}$.

Since species $\mathcal{A}$ and $\mathcal{B}$ are involatile, the corresponding interfacial fluxes must vanish, viz., $\mathbf{f}_{\mathcal{A}} = \mathbf{f}_{\mathcal{B}} = 0$. Hence, the interfacial mass balances (15) for species $\mathcal{A}$ and $\mathcal{B}$ reduce to

$$[\varrho_{\mathcal{A}}] = [\varrho_{\mathcal{B}}] = 0, \quad (98)$$

from which it follows that

$$(\varrho_{\mathcal{A}}^s)_- = \varrho_{\mathcal{A}}^{\text{eq}} \quad \text{and} \quad (\varrho_{\mathcal{B}}^s)_- = \varrho_{\mathcal{B}}^{\text{eq}}, \quad (99)$$

where φ_-^s denotes the interfacial value of a field φ^s defined in the crystalline region (see Section II). On the other hand, the interfacial mass balance for the solvent is still given by

$$-[\varrho_{\mathcal{S}}]V^{\text{mig}} = \mathbf{f}_{\mathcal{S}}. \quad (100)$$

Since it is unconstrained by the interfacial dissipation inequality (71), $\mathbf{f}_{\mathcal{S}}$ is constitutively indeterminate. Hence, (100) serves to specify the values that $\mathbf{f}_{\mathcal{S}}$ can take such that the interfacial mass balance for the solvent holds.

Under the assumptions that the solvent evaporates at the phase boundary and that the solutes are involatile, the interfacial momentum balance (30) takes the form of the Young–Laplace equation

$$-[\mathcal{P}] + \sigma\kappa = 0. \quad (101)$$

When the radius of the spherulite is sufficiently large that the effect of the line tension can be ignored, (101) reduces to the condition that the pressure be continuous across the phase boundary. In view of the statement contained in the paragraph that follows (97) and of (99), this condition takes the form

$$p^s(\varrho_{\mathcal{A}}^{\text{eq}}, \varrho_{\mathcal{B}}^{\text{eq}}, (\varrho_{\mathcal{S}}^s)_-) = p^a(\varrho_{\mathcal{A}}^{\text{eq}}, \varrho_{\mathcal{B}}^{\text{eq}}, \varrho_{\mathcal{S}}^{\text{eq}}), \quad (102)$$

which may be solved for the interfacial value $(\varrho_{\mathcal{S}}^s)_-$ of the density of solvent in the crystalline region. Hence, (99) and (102) determine the limiting values of the densities of all three species as the interface is approached from within the spherulitic phase. Importantly, as a consequence of the neglect of deformation in the amorphous region and of line-tension effects at the phase boundary, these values are constant.

C. Constant growth rate

We now turn to (73). Upon neglecting the interfacial viscosity γ , the line tension and free-energy density of the phase boundary coincide,

$$\sigma = \psi. \quad (103)$$

Hence, in view of (62) and (103), the Young–Laplace equation (101) can be rewritten as

$$[\omega] + \psi\kappa = 0. \quad (104)$$

It follows that the kinetic relation (72) reduces to

$$[(\mu_i - \mu_i^v)\varrho_i] = \beta V^{\text{mig}}. \quad (105)$$

Consistent with the neglect of deformation in the amorphous phase, if we now assume that the growth rate V is much larger than $\mathbf{v} \cdot \mathbf{n}$, (105) takes the form

$$V \simeq \frac{1}{\beta} [(\mu_i - \mu_i^v)\varrho_i]. \quad (106)$$

Since the kinetic coefficient β is a parameter pertaining to the propagating interface, for a given temperature Θ it should be determined by $(\varrho_{\mathcal{A}}^s)_-$, $(\varrho_{\mathcal{B}}^s)_-$, $(\varrho_{\mathcal{S}}^s)_-$, $(\varrho_{\mathcal{A}}^a)_+$, $(\varrho_{\mathcal{B}}^a)_+$, and $(\varrho_{\mathcal{S}}^a)_+$, which are in turn determined through (75), (89), (90), (99), and (102), by $\varrho_{\mathcal{A}}^*$, $\varrho_{\mathcal{B}}^*$, and $p_{\mathcal{S}}^v$. Thus β is constant in time for a film that undergoes spherulitic crystallization at a constant temperature upon exposure to solvent vapor with a fixed partial pressure $p_{\mathcal{S}}^v$. By the same argument, the jump $[(\mu_i - \mu_i^v)\varrho_i]$ is also constant in time. Hence, when the radius of the spherulite is large and the effect of line tension is negligible, the velocity V of the interface separating the amorphous and crystalline phases is constant.

This constant growth rate is a central feature of spherulitic crystallization. It is therefore worth noting that this result holds regardless of the chemical nature (small molecules, polymers, etc.) of the binary thin-film blend, provided that the assumptions made (involatile solutes, negligible deformation of an amorphous phase in chemical equilibrium with the vapor, absence of any significant line-tension effects, etc.) are valid.

Finally, note that with constant velocity the shape of the crystalline region tends to that of a spherulite. Indeed, assume that the crystalline region $\Omega^s(t)$ has at some instant t the shape of an ellipse with semi-axes a and b ($a < b$). Then, at $t + \delta t$ the boundary points on the semi-minor and semi-major axes will be at distances $a + V\delta t$ and $b + V\delta t$ away from the origin, respectively. Thus, as δt increases the ratio between these two distances will approach one. As time passes, the crystalline region will therefore acquire the shape of a disk.

IX. SPHERULITIC GROWTH IN BINARY FILMS INDUCED BY RESIDUAL SOLVENT

In the work of Lloyd *et al.* [7], the experimental setup is different than that of [8, 16, 28]. After spin coating in air, each film that consists of involatile solutes $\mathcal{A}$ and $\mathcal{B}$ as well as residual solvent $\mathcal{S}$ is immediately transferred into a container, which was then sealed tight. Spherulitic crystallization, which is induced by the residual solvent

left in the spin-coated film, begins shortly thereafter. The duration of spherulitic growth that is of interest to us lasts no more than three minutes.

As in the preceding section we consider crystallization of an isolated spherulite, and we assume that the as-spun film is both amorphous and homogeneous. Let $\varrho_{\mathcal{A}}^*$, $\varrho_{\mathcal{B}}^*$, and $\varrho_{\mathcal{S}}^*$ be the uniform densities of species $\mathcal{A}$, species $\mathcal{B}$, and residual solvent $\mathcal{S}$ in the as-spun film, respectively. Let t be the time elapsed since the spherulite begins to form and $(0, T]$ the time interval of interest. Because the residual solvent in the film is what remains in the film *after* spin-coating, we assume that evaporation of solvent during the period $(0, T]$ of interest is negligible. In other words, we take $K_{\mathcal{S}}^a \simeq 0$ in the mass balance (76) and momentum balance (78). We further assume that deformation in the amorphous region is negligible. Then we have

$$\varrho_i^a = \varrho_i^* \quad (i = \mathcal{A}, \mathcal{B}, \mathcal{S}) \quad (107)$$

everywhere in the amorphous region during the time interval $(0, T]$. Note that, in view of (91) and (107), when the amounts of solvent present in the film are negligible, the densities of species $\mathcal{A}$ and $\mathcal{B}$ in the amorphous region coincide with their initial values, provided that the deformation in the region in question is negligibly small and irrespective of whether spherulitic crystallization is triggered by exposure to solvent vapor, as in [8, 16, 28], or induced by residual solvent, as in [7].

In the crystalline region the equations that govern motion and the densities ϱ_i^s ($i = \mathcal{A}, \mathcal{B}, \mathcal{S}$) are the same as those given in the preceding section; see (94) onward. Indeed the discussion that leads to the formula (106) for the spherulitic growth rate V remains exactly the same, with the initial densities in place of their equilibrium counterparts. We therefore refrain from repeating it here.

X. GROWTH RATE DEPENDENCE ON THE ADDITIVE MOLE FRACTION

Herein we return to the setting of Section VIII. However we restrict our attention to as-spun films where the species $\mathcal{A}$ and $\mathcal{B}$ are in *solution* and the mole fraction of $\mathcal{B}$ is small. We therefore call species $\mathcal{A}$ the solute and species $\mathcal{B}$ the additive.

We shall find it convenient to work with mole-number densities instead of mass densities. Accordingly, recalling that w_i is the molecular weight of the i th species, we introduce its areal mole-number density

$$n_i^\alpha = \frac{\varrho_i^\alpha}{w_i} \quad (i = \mathcal{A}, \mathcal{B}, \mathcal{S}) \quad (108)$$

in the α phase. In addition, we write $\tilde{\Psi}^\alpha$ for the free-energy density of the α phase as a function of the molar densities of its constituents, viz.,

$$\tilde{\Psi}^\alpha(n_{\mathcal{A}}^\alpha, n_{\mathcal{B}}^\alpha, n_{\mathcal{S}}^\alpha) = \Psi^\alpha(w_{\mathcal{A}}n_{\mathcal{A}}^\alpha, w_{\mathcal{B}}n_{\mathcal{B}}^\alpha, w_{\mathcal{S}}n_{\mathcal{S}}^\alpha), \quad (109)$$

and $\tilde{\mu}_i^\alpha$ for the *molar* chemical potential of the i th species in the α phase

$$\tilde{\mu}_i^\alpha = \frac{\partial \tilde{\Psi}^\alpha}{\partial n_i^\alpha}. \quad (110)$$

By (59), (110), and the chain rule, we have $\mu_i^\alpha = \tilde{\mu}_i^\alpha/w_i$, from which it follows that $\varrho_i^\alpha \mu_i^\alpha = n_i^\alpha \tilde{\mu}_i^\alpha$ (no summation over the repeated index i here).

Let n^α be the total mole-number density in the α phase,

$$n^\alpha = n_{\mathcal{A}}^\alpha + n_{\mathcal{B}}^\alpha + n_{\mathcal{S}}^\alpha, \quad (111)$$

and denote by

$$x_i^\alpha = \frac{n_i^\alpha}{n^\alpha} \quad (i = \mathcal{A}, \mathcal{B}, \mathcal{S}) \quad (112)$$

the mole fraction of the i th species in the α phase. From (111) and (112), it follows that only two of the species mole fractions, say, $x_{\mathcal{A}}^\alpha$ and $x_{\mathcal{B}}^\alpha$, are independent, with the third, $x_{\mathcal{S}}^\alpha$, given by

$$x_{\mathcal{S}}^\alpha = 1 - x_{\mathcal{A}}^\alpha - x_{\mathcal{B}}^\alpha. \quad (113)$$

Moreover, we assume that throughout the time interval of interest $n_{\mathcal{S}}^\alpha$ remains everywhere minuscule, viz.,

$$n_{\mathcal{S}}^\alpha \simeq 0, \quad (114)$$

so that

$$n^\alpha \simeq n_{\mathcal{A}}^\alpha + n_{\mathcal{B}}^\alpha. \quad (115)$$

Further, by (108) and (98),

$$[n_{\mathcal{A}}] = [n_{\mathcal{B}}] = 0. \quad (116)$$

Importantly, in view of (91), (108), (114), and (116), the molar densities of species $\mathcal{A}$ and $\mathcal{B}$ coincide at the phase boundary with their initial values, viz.,

$$(n_i^s)_- = (n_i^a)_+ \simeq n_i^* = \frac{\varrho_i^*}{w_i}, \quad i = \mathcal{A}, \mathcal{B}. \quad (117)$$

In view of (106), the rate of spherulitic growth V is given by the formula

$$\beta V = [\varrho_i \mu_i] - [\varrho_{\mathcal{S}} \mu_{\mathcal{S}}^v] = [n x_i \tilde{\mu}_i] - w_{\mathcal{S}} \mu_{\mathcal{S}}^v [n_{\mathcal{S}}], \quad (118)$$

where β was introduced in (72), $\tilde{\mu}_i^\alpha$ is given by (110), and $\mu_{\mathcal{S}}^v$ is defined by (74). As pointed out in Section VIII (see the paragraph that immediately follows (106)), for a given temperature Θ the kinetic coefficient β is determined by $\varrho_{\mathcal{A}}^*$, $\varrho_{\mathcal{B}}^*$, and $p_{\mathcal{S}}^v$. For the set of experiments under consideration the kinetic coefficient β is expected to assume different values as the partial pressure $p_{\mathcal{S}}^v$ of the solvent vapor is made to vary from experiment to experiment. If we denote by

$$g^\alpha = x_{\mathcal{A}}^\alpha \tilde{\mu}_{\mathcal{A}}^\alpha + x_{\mathcal{B}}^\alpha \tilde{\mu}_{\mathcal{B}}^\alpha + x_{\mathcal{S}}^\alpha \tilde{\mu}_{\mathcal{S}}^\alpha$$

the molar Gibbs free energy of the ternary mixture in the α phase, (118) can be rewritten as

$$\beta V = \llbracket ng \rrbracket - w_s \mu_s^v \llbracket n_s \rrbracket \simeq \llbracket ng \rrbracket, \quad (119)$$

since, in view of (114), $\llbracket n_s \rrbracket \simeq 0$. Hence, when the molar density of the solvent is negligibly small, the driving force for crystallization reduces to the jump in the Gibbs free energy across the interface separating the spherulitic and amorphous phases.

In the amorphous phase, the three species are assumed to be in solution. Let g_i^a be the molar Gibbs free energy of pure i th species in the amorphous region and denote by $g^{E,a}$ the excess molar Gibbs free energy. The molar Gibbs free energy of the mixture in the amorphous region Ω^a is given by

$$g^a = x_i^a g_i^a + R\Theta x_i^a \ln x_i^a + g^{E,a}(x_{\mathcal{A}}^a, x_{\mathcal{B}}^a, x_s^a), \quad (120)$$

where summation over the repeated index i is implied and the excess molar Gibbs free energy $g^{E,a}$ satisfies the condition

$$g^{E,a}(1, 0, 0) = 0. \quad (121)$$

Introducing

$$\tilde{g}^{E,a}(x_{\mathcal{A}}^a, x_{\mathcal{B}}^a) := g^{E,a}(x_{\mathcal{A}}^a, x_{\mathcal{B}}^a, 1 - x_{\mathcal{A}}^a - x_{\mathcal{B}}^a) \quad (122)$$

and taking the linear approximation of $g^{E,a}$ at $(x_{\mathcal{A}}^a, x_{\mathcal{B}}^a, x_s^a) = (1, 0, 0)$, we obtain

$$g^{E,a} \simeq \Phi_{\mathcal{A}}^a (x_{\mathcal{A}}^a - 1) + \Phi_{\mathcal{B}}^a x_{\mathcal{B}}^a, \quad (123)$$

where Φ_i^a ($i = \mathcal{A}, \mathcal{B}$) is defined by

$$\Phi_i^a := \frac{\partial \tilde{g}^{E,a}}{\partial x_i^a}(1, 0) = \left(\frac{\partial g^{E,a}}{\partial x_i^a} - \frac{\partial g^{E,a}}{\partial x_s^a} \right)(1, 0, 0). \quad (124)$$

Since by (114) $x_s^a \simeq 0$, we approximate g^a by putting $x_s^a = 0$ and $x_{\mathcal{A}}^a = 1 - x_{\mathcal{B}}^a$ in (120) and (123), therefore obtaining the following expression for the Gibbs free energy of the amorphous phase

$$g^a \simeq (1 - x_{\mathcal{B}}^a) g_{\mathcal{A}}^a + x_{\mathcal{B}}^a g_{\mathcal{B}}^a + (\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a) x_{\mathcal{B}}^a + R\Theta((1 - x_{\mathcal{B}}^a) \ln(1 - x_{\mathcal{B}}^a) + x_{\mathcal{B}}^a \ln x_{\mathcal{B}}^a), \quad (125)$$

with $\Phi_{\mathcal{A}}^a$ and $\Phi_{\mathcal{B}}^a$ given by (124). The last term on the right-hand side of (125) is the drop in the molar Gibbs free energy due to the entropy of mixing. The term $(\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a) x_{\mathcal{B}}^a$ is the linear approximation to the excess molar free energy $g^{E,a}$ when $x_{\mathcal{B}}^a$ is small and x_s^a is minuscule and ignored. It describes deviation from ideal-solution behavior and can be either positive or negative as determined by the sign of the factor $\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a$. Specifically, if $\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a > 0$, the contribution of the term $(\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a) x_{\mathcal{B}}^a$ to the molar Gibbs free energy g^a is positive. If this positive contribution is larger than the decrease in g^a due to the entropy of mixing, species $\mathcal{A}$ and $\mathcal{B}$ will demix. Thus we can say that the larger is the factor $\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a$, the higher is the propensity for demixing of the binary solution.

We divide our further discussions into two cases.

A. The spherulitic phase as a solid solution

Assume that the solute $\mathcal{A}$ and the additive $\mathcal{B}$ remain in solution in the spherulitic phase. The specific Gibbs free energy of the solution in the spherulitic phase then obeys a formula of the same form as (125). Moreover, in view of (114)–(116), we have

$$\llbracket n_s \rrbracket \simeq 0, \llbracket n \rrbracket \simeq \llbracket n_{\mathcal{A}} + n_{\mathcal{B}} \rrbracket = 0, \llbracket x_{\mathcal{B}} \rrbracket \simeq 0. \quad (126)$$

In view of (91), (99), (108) and (112), it follows from (126)₃ that

$$(x_{\mathcal{B}}^s)_- \simeq (x_{\mathcal{B}}^a)_+ \simeq x_{\mathcal{B}}^*, \quad (127)$$

where $x_{\mathcal{B}}^*$ denotes the as-spun value of $x_{\mathcal{B}}$ after thermal annealing. Hence, on appealing to (125) and (126), (119) delivers the following approximate formula for the spherulitic growth rate:

$$\begin{aligned} V &\simeq \frac{n}{\beta} \llbracket (1 - x_{\mathcal{B}}) g_{\mathcal{A}} + x_{\mathcal{B}} g_{\mathcal{B}} + (\Phi_{\mathcal{B}} - \Phi_{\mathcal{A}}) x_{\mathcal{B}} \rrbracket \\ &= \frac{n}{\beta} \left\{ \llbracket g_{\mathcal{A}} \rrbracket - (\llbracket g_{\mathcal{A}} \rrbracket - \llbracket g_{\mathcal{B}} \rrbracket - \llbracket \Phi_{\mathcal{B}} - \Phi_{\mathcal{A}} \rrbracket) x_{\mathcal{B}}^* \right\}. \end{aligned} \quad (128)$$

Under the present scenario, if the spherulitic growth rate V is measured, for a given set of total pressure p^v of the gas mixture, partial pressure p_s^v of the solvent vapor, and temperature Θ , on various films which have different (but small) as-spun mole fractions $x_{\mathcal{B}}^*$ of additive, a plot of V as a function of $x_{\mathcal{B}}^*$ will give a straight line with intercept equal to $n \llbracket g_{\mathcal{A}} \rrbracket / \beta$, where $\llbracket g_{\mathcal{A}} \rrbracket = \tilde{\mu}_{\mathcal{A}}^a - \tilde{\mu}_{\mathcal{A}}^s$ is the difference in the molar chemical potential of pure $\mathcal{A}$ between the as-spun and its spherulitic phases.

As for the slope, we expect that $\llbracket g_{\mathcal{B}} \rrbracket = 0$ if the additive $\mathcal{B}$ undergoes no phase change upon crystallization of the solute $\mathcal{A}$, and that $\llbracket \Phi_{\mathcal{B}} - \Phi_{\mathcal{A}} \rrbracket < 0$ if the excess molar Gibbs free energies would give the crystallized phase a stronger propensity than the amorphous phase for species $\mathcal{A}$ and $\mathcal{B}$ to demix; cf. the discussion that immediately follows (125). Under such physically plausible assumptions the linear plot of V vs. $x_{\mathcal{B}}^*$ will have a negative slope.

B. Unmixed solute and additive in the spherulitic phase

Here, we assume that the solute $\mathcal{A}$ and the additive $\mathcal{B}$ become unmixed in the spherulitic phase. Specifically, we consider two distinct scenarios. In the first scenario, which we refer to as lateral separation, the additive molecules remain trapped between the fibers of the spherulite. The fibers are made of crystallized solute and the additive is either in its crystalline or amorphous state. In the second scenario, which we call vertical separation, the additive segregates to either one or both interfaces separating the spherulite from the vapor and substrate. As with the first scenario, the additive can remain in its amorphous phase or it can crystallize.

Lateral segregation inside of the spherulitic regions was reported by Lloyd *et al.* [7] in thin films made of anthradithiophene (ethyl-TES ADT) and fullerene (PCBM), whereas vertical separation has been observed in thin-film blends of small molecules and polymers such as P3HT-PCBM (see [2] and the references therein) and TES ADT-PαMS [31]. Thus, either lateral or vertical segregation of the additive can occur. A two-dimensional theory such as ours, however, cannot distinguish between lateral and vertical segregations, as the thin film is modeled to have zero thickness. A third possible scenario would consist of the lateral expulsion of additive molecules from the spherulite into the amorphous region. This would require the diffusive transport inside the spherulite of additive molecules toward the phase boundary. Moreover, the resulting accumulation of additive in front of the propagating interface would trigger the diffusion of additive molecules away from the interface into the amorphous region. Since we do not allow for diffusion of any species, this scenario goes beyond the scope of the present theory and is left for future work.

In either lateral or vertical segregation, with $\mathcal{A}$ and $\mathcal{B}$ unmixed, the specific Gibbs free energy of the spherulitic phase is given approximately by

$$g^s \simeq (1 - x_{\mathcal{B}}^s)g_{\mathcal{A}}^s + x_{\mathcal{B}}^s g_{\mathcal{B}}^s, \quad (129)$$

where g_i^s is the molar Gibbs free energy of pure i th species in the crystallized phase. The spherulitic growth-rate formula (119) then becomes

$$V \simeq \frac{n}{\beta} \left\{ \llbracket g_{\mathcal{A}} \rrbracket - (\llbracket g_{\mathcal{A}} \rrbracket - \llbracket g_{\mathcal{B}} \rrbracket - (\Phi_{\mathcal{B}}^a - \Phi_{\mathcal{A}}^a))x_{\mathcal{B}}^* \right. \\ \left. + R\Theta((1 - x_{\mathcal{B}}^*)\ln(1 - x_{\mathcal{B}}^*) + x_{\mathcal{B}}^*\ln x_{\mathcal{B}}^*) \right\}. \quad (130)$$

In (130), the term $R\Theta((1 - x_{\mathcal{B}}^*)\ln(1 - x_{\mathcal{B}}^*) + x_{\mathcal{B}}^*\ln x_{\mathcal{B}}^*)$, which is the drop in the molar Gibbs free energy due to the entropy of mixing, is zero at $x_{\mathcal{B}}^* = 0$, negative for $x_{\mathcal{B}}^* > 0$, and has a steep negative slope near $x_{\mathcal{B}}^* = 0$. Hence, in a plot of V versus $x_{\mathcal{B}}^*$, there will be an abrupt drop of V in the vicinity of $x_{\mathcal{B}}^* = 0$ from its value at $x_{\mathcal{B}}^* = 0$.

C. Discussion

For each experiment [8, 16, 28] to measure the spherulitic growth rate V in a given film, the temperature Θ is fixed, and so are the total gas pressure p^v , the partial pressure p_s^v of the solvent vapor, and the as-spun molar densities $n_{\mathcal{A}}^*$, $n_{\mathcal{B}}^*$. Under the approximation $n_{\mathcal{S}}^s \simeq 0$, which we adopt in (114) above, $n \simeq n_{\mathcal{A}}^* + n_{\mathcal{B}}^*$ is approximately a constant; so is $x_{\mathcal{B}}^* = n_{\mathcal{B}}^*/n$. By (101), (102) and (115), when the radius of the spherulite is sufficiently large that the effect of line tension can be ignored, we have

$$p_-^s = p_+^a = p^a(n_{\mathcal{A}}^{\text{eq}}, n_{\mathcal{B}}^{\text{eq}}, n_{\mathcal{S}}^{\text{eq}}) \simeq p^a(n_{\mathcal{A}}^*, n_{\mathcal{B}}^*, 0). \quad (131)$$

The molar Gibbs free energies $g_{\mathcal{A}}^a$ and $g_{\mathcal{B}}^a$ for pure solute and additive in phase α are functions of the temperature Θ and the two-dimensional film tension $-p^a$ or equivalently p^a ($\alpha = a, s$). By (131), we observe that for a given Θ , and for $i = \mathcal{A}, \mathcal{B}$, the jump in molar Gibbs free energy

$$\llbracket g_i \rrbracket = (g_i^a)_+ - (g_i^s)_- = g_i^a(p_+^a) - g_i^s(p_-^s) \quad (132)$$

is a fixed real number. For $\alpha = a, s$, the quantities $\Phi_{\mathcal{A}}^a$ and $\Phi_{\mathcal{B}}^a$, as defined by (124), depend only on the temperature Θ . Earlier, we have already seen (see the discussion that immediately follows (106)) that for a given temperature Θ the kinetic coefficient β is determined by $n_{\mathcal{A}}^*$, $n_{\mathcal{B}}^*$, and p_s^v , which are constants for a specific experiment conducted on a given film. Hence, all the quantities on the right-hand sides of (128) and (130) are specified real numbers. Spherulites therefore crystallize at a constant rate in both of these cases.

From (128) and (130) we observe that solvent vapor would affect the spherulitic growth rate V only through its effect on the kinetic coefficient β . In particular, for experiments that differ only in the partial pressure p_s^v of the solvent vapor, if $1/\beta$ is a linear function of p_s^v , the growth rate V will be a linear function of p_s^v . Given our assumption that the vapor is an ideal gas, this observation is consistent with experimental measurements of growth rate of TES ADT spherulites vs. concentration of DCE solvent vapor in the gas stream (see Fig. S3 in the Supporting Information for Lee *et al.* [16]).

XI. CONCLUDING REMARKS

A sharp-interface theory for the spherulitic crystallization at fixed temperature of a spin-coated, binary, thin-film blend under solvent-vapor annealing is derived from the basic principles of continuum thermomechanics. Central to the proposed theory is the assumption that growth is interface-driven, in contrast to existing models which, following Keith and Padden [25], all assume that crystallization occurs in the presence of diffusion (Goldenfeld [26], Gránásky *et al.* [27]). The proposed theory is thermodynamically consistent in the sense that all constitutive relations are compatible with the first and second laws. Its main result is a kinetic relation linking the velocity of the phase boundary relative to that of the underlying thin film to the driving force for crystallization.

A universal feature of spherulitic crystallization is that growth is linear in time. A theory of spherulitic growth should therefore deliver a constant growth rate for the crystalline phase. This is indeed what the proposed theory predicts. Under several physically plausible assumptions (involatile solutes, negligible deformation of an amorphous phase in chemical equilibrium with the vapor, absence of any significant effects due to shear stress and line tension), the aforementioned kinetic relation yields a constant interfacial velocity. Whether the phase transition retains its spherulitic character in

the presence of molecular diffusion or on relaxing any of the aforementioned assumptions remains open to investigation. Furthermore, the influence of the substrate on spherulitic crystallization remains to be understood, e.g., the nonmonotonic dependence of the growth rate on the energy of the interface separating film from substrate (see Lee et al. [16], Fig. 1).

When the concentration of solvent remains everywhere minuscule in the film, in the proposed theory the driving force for crystallization reduces to the jump in the Gibbs free energy across the phase boundary. When the theory is further specialized to thin-film blends in which one component (the additive) has a small mole fraction, formulas are derived which show how the mole fraction of the additive affects spherulitic growth rates for the two cases where the major component (the solute) and the additive (i) remain in solution and (ii) become segregated within the spherulitic phase. These formulas will serve as the theoretical basis for the explanation and interpretation of some recent [8] and new experimental findings in a forthcoming paper [28].

Acknowledgments

We thank Yueh-Lin Loo and John E. Anthony for helpful discussions pertaining to their experimental findings on spherulitic growth in organic semiconductor thin films. The research reported here was supported in part by the SOLAR Initiative of the National Science Foundation, USA, through grant DMR-1035257.

Appendix A: Transport identities

Our goal here is to establish the transport relations (8) and (11). In deriving (8), our starting point is the standard transport theorem which, for any migrating region $\mathcal{R}(t)$ whose boundary is endowed with the normal velocity $V_{\partial\mathcal{R}}^\perp$ and for any scalar field ϕ smooth up to the interface (across which it suffers a jump discontinuity), takes the form

$$\frac{d}{dt} \int_{\mathcal{R}} \phi \, da = \int_{\mathcal{R}} \frac{\partial \phi}{\partial t} \, da + \int_{\partial\mathcal{R}} \phi V_{\partial\mathcal{R}}^\perp \, ds - \int_{\Sigma} [\![\phi]\!] V \, ds. \quad (\text{A.1})$$

Let $\phi = \varrho\varphi$. On account of the mass balance (19), (A.1) can be rewritten as

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \varrho\varphi \, da &= \int_{\mathcal{R}} \left(\varrho \frac{\partial \varphi}{\partial t} - \varphi(\nabla \cdot (\varrho\mathbf{v}) - F) \right) da \\ &\quad + \int_{\partial\mathcal{R}} \varrho\varphi V_{\partial\mathcal{R}}^\perp \, ds - \int_{\Sigma} [\![\varrho\varphi]\!] V \, ds. \end{aligned} \quad (\text{A.2})$$

Next, appealing to the definition of the material time derivative of a scalar field (6)₁ and using the divergence

theorem, (A.2) reduces to the transport identity (8), viz.,

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \varrho\varphi \, da &= \int_{\mathcal{R}} (\varrho\dot{\varphi} + \varphi F) \, da \\ &\quad + \int_{\partial\mathcal{R}} \varrho\varphi V_{\partial\mathcal{R}}^{\text{mig}} \, ds - \int_{\Sigma} [\![\varrho\varphi]\!] V^{\text{mig}} \, ds, \end{aligned} \quad (\text{A.3})$$

where V^{mig} and $V_{\partial\mathcal{R}}^{\text{mig}}$ are defined by (3) and (2).

An identical transport relation for vector fields can be derived along the same lines.

To derive the interfacial transport identity (11), we begin with the standard transport theorem for line integrals as it applies to a constant integrand,

$$\frac{d}{dt} \int_{\Sigma} ds = - \int_{\Sigma} \kappa V \, ds + \int_{\partial\Sigma} \mathbf{v}_{\partial\Sigma} \cdot \mathbf{t}, \quad (\text{A.4})$$

where

$$\int_{\partial\Sigma} \mathbf{v}_{\partial\Sigma} \cdot \mathbf{t} = \dot{\mathbf{x}}_1 \cdot \mathbf{t}_1 - \dot{\mathbf{x}}_0 \cdot \mathbf{t}_0. \quad (\text{A.5})$$

By the Frenet relation (1) and the fundamental theorem for line integrals, (A.5) can be rewritten as

$$\int_{\partial\Sigma} \mathbf{v}_{\partial\Sigma} \cdot \mathbf{t} = \int_{\partial\Sigma} \mathbf{v}_{\partial\Sigma}^{\text{mig}} \cdot \mathbf{t} + \int_{\Sigma} \left(\frac{\partial \mathbf{v}}{\partial s} \cdot \mathbf{t} + \kappa \mathbf{v} \cdot \mathbf{n} \right) ds, \quad (\text{A.6})$$

where the first integral on the right-hand side is given by (12). Finally, substituting (A.6) in (A.4) and invoking (2) yields the desired relation (11).

Appendix B: Angular momentum balance and the tangential character of the interfacial Cauchy stress vector

The purpose of this appendix is to derive the tangential character of the Cauchy stress vector associated with the phase boundary from the balance of angular momentum. This balance requires that, for any evolving region $\mathcal{R}$ of the film, the rate at which the angular momentum changes be balanced by the sum of the moments exerted on $\mathcal{R}$ by external agencies, augmented by the flow of angular momentum that accompanies evaporation-condensation and the migration of the boundary $\partial\mathcal{R}$. Specifically,

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \varrho \mathbf{x} \times \mathbf{v} \, da - \int_{\partial\mathcal{R}} \varrho \mathbf{x} \times \mathbf{v} V_{\partial\mathcal{R}}^{\text{mig}} \, ds &= \\ - \int_{\partial\mathcal{R}} \mathbf{x} \times p \mathbf{n}_{\partial\mathcal{R}} \, ds + \int_{\mathcal{R}} \mathbf{x} \times \mathbf{T} \mathbf{e} \, da - \int_{\mathcal{R}} \mathbf{x} \times p^v \mathbf{e} \, da \\ + \int_{\partial\Sigma} \mathbf{x} \times \boldsymbol{\sigma} + \int_{\mathcal{R}} \mathbf{x} \times \mathbf{u}_i F_i \, da + \int_{\Sigma} \mathbf{x} \times \mathbf{u}_i \mathbf{f}_i \, ds, \end{aligned} \quad (\text{B.1})$$

where $\mathbf{x}$ denotes the position vector of a generic point of the film in $\mathcal{R}$ and summation over the repeated index i is implied. The second integral on the left-hand side of (B.1) accounts for the flow of angular momentum into or out of $\mathcal{R}$ that results from the migration of its boundary. The last two integrals on the right-hand side of (B.1) represent the flow of angular momentum that accompanies evaporation-condensation of the constituents of the film away and at the portion Σ of the phase boundary.

In view of the transport identity (8) and of the interfacial mass balance (17), the left-hand side of (B.1) takes the form

$$\begin{aligned} \frac{d}{dt} \int_{\mathcal{R}} \rho \mathbf{x} \times \mathbf{v} da - \int_{\partial \mathcal{R}} \rho \mathbf{x} \times \mathbf{v} ds = \\ \int_{\mathcal{R}} (\rho \mathbf{x} \times \dot{\mathbf{v}} + \mathbf{x} \times \mathbf{v} F) da + \int_{\Sigma} \mathbf{x} \times \mathbf{v} f ds, \end{aligned} \quad (\text{B.2})$$

where, in applying (8), we make use of the definition $\dot{\mathbf{x}} = \mathbf{v}$, from which it follows that $\dot{\mathbf{x}} \times \mathbf{v} = \mathbf{0}$.

We now take the cross product of each of the terms of (B.1) with a constant vector $\mathbf{a}$ and make use of the identity

$$\mathbf{a} \times (\mathbf{b} \times \mathbf{c}) = (\mathbf{b} \otimes \mathbf{c} - \mathbf{c} \otimes \mathbf{b})\mathbf{a}, \quad (\text{B.3})$$

which holds for any choice of vectors $\mathbf{a}$, $\mathbf{b}$, and $\mathbf{c}$. In view of (B.2) and (B.3), the cross product of the left-hand side of (B.1) with $\mathbf{a}$ can be written as

$$\begin{aligned} \mathbf{a} \times \left(\frac{d}{dt} \int_{\mathcal{R}} \rho \mathbf{x} \times \mathbf{v} da - \int_{\partial \mathcal{R}} \rho \mathbf{x} \times \mathbf{v} ds \right) = \\ \int_{\mathcal{R}} \{ \rho (\mathbf{x} \otimes \dot{\mathbf{v}} - \dot{\mathbf{v}} \otimes \mathbf{x}) + (\mathbf{x} \otimes \mathbf{v} - \mathbf{v} \otimes \mathbf{x}) F \} \mathbf{a} da \\ + \int_{\Sigma} (\mathbf{x} \otimes \mathbf{v} - \mathbf{v} \otimes \mathbf{x}) \mathbf{a} f ds. \end{aligned} \quad (\text{B.4})$$

Similarly, taking the cross product of $\mathbf{a}$ with the first integral on the right-hand side of (B.1) and invoking (B.3) and the divergence theorem, we get

$$\begin{aligned} -\mathbf{a} \times \int_{\partial \mathcal{R}} \mathbf{x} \times p \mathbf{n}_{\partial \mathcal{R}} ds = - \int_{\mathcal{R}} (\mathbf{x} \otimes \nabla p - \nabla p \otimes \mathbf{x}) \mathbf{a} da \\ + \int_{\Sigma} (\mathbf{x} \otimes [p] \mathbf{n} - [p] \mathbf{n} \otimes \mathbf{x}) \mathbf{a} ds. \end{aligned} \quad (\text{B.5})$$

Further, taking the cross product of $\mathbf{a}$ with the second and third integrals on the right-hand side of (B.1) and appealing to (21) and (B.3), we obtain

$$\begin{aligned} \mathbf{a} \times \int_{\mathcal{R}} \mathbf{x} \times (\tau - p^v) \mathbf{e} da = \\ \int_{\mathcal{R}} \{ \mathbf{x} \otimes (\tau - p^v) \mathbf{e} - (\tau - p^v) \mathbf{e} \otimes \mathbf{x} \} \mathbf{a} da. \end{aligned} \quad (\text{B.6})$$

Next, taking the cross product of $\mathbf{a}$ with the fourth integral on the right hand side of (B.1) and making use of (B.3), the fundamental theorem for line integrals, and the definition $\mathbf{t} = \partial \mathbf{x} / \partial s$ of the unit tangent to the phase boundary, we get

$$\begin{aligned} \mathbf{a} \times \int_{\partial \Sigma} \mathbf{x} \times \boldsymbol{\sigma} = \int_{\Sigma} (\mathbf{t} \otimes \boldsymbol{\sigma} - \boldsymbol{\sigma} \otimes \mathbf{t}) \mathbf{a} ds \\ + \int_{\Sigma} \left(\mathbf{x} \otimes \frac{\partial \boldsymbol{\sigma}}{\partial s} - \frac{\partial \boldsymbol{\sigma}}{\partial s} \otimes \mathbf{x} \right) \mathbf{a} ds. \end{aligned} \quad (\text{B.7})$$

Further, taking the cross product of $\mathbf{a}$ with the last two terms of (B.1) and invoking once more (B.3), we have

$$\begin{cases} \mathbf{a} \times \int_{\mathcal{R}} \mathbf{x} \times \mathbf{u}_i F_i da = \int_{\mathcal{R}} (\mathbf{x} \otimes \mathbf{u}_i - \mathbf{u}_i \otimes \mathbf{x}) \mathbf{a} F_i da, \\ \mathbf{a} \times \int_{\Sigma} \mathbf{x} \times \mathbf{u}_i f_i ds = \int_{\Sigma} (\mathbf{x} \otimes \mathbf{u}_i - \mathbf{u}_i \otimes \mathbf{x}) \mathbf{a} f_i ds. \end{cases} \quad (\text{B.8})$$

Combining (B.2)–(B.8) and appealing to the momentum balances (26) and (29), we are left with

$$\int_{\Sigma} (\mathbf{t} \otimes \boldsymbol{\sigma} - \boldsymbol{\sigma} \otimes \mathbf{t}) \mathbf{a} ds = \mathbf{0}, \quad (\text{B.9})$$

for any choice of subcurve Σ of Γ and for any choice of constant vector $\mathbf{a}$. It follows that

$$\boldsymbol{\sigma} \otimes \mathbf{t} = \mathbf{t} \otimes \boldsymbol{\sigma} \quad (\text{B.10})$$

everywhere along the phase boundary. This is equivalent to the requirement that the line tension be tangential to the phase boundary, i.e.,

$$\boldsymbol{\sigma} = \sigma \mathbf{t}. \quad (\text{B.11})$$

Appendix C: Thermodynamic analysis of the evaporation-condensation of a multicomponent thin film

Recall that the thermodynamic system $\mathcal{R}(t)$, as introduced in Section V, consists at each time t of the union of the part of the film defined by $\mathcal{R}(t)$ and the molecules which at time t are condensing on or evaporating from $\mathcal{R}(t)$. The objective of the present thermodynamic analysis is to provide a rationale for the form (32) that the power expended on $\mathcal{R}(t)$ by external agencies takes, for the expressions (38) and (40) of the energy and entropy flows into or out of $\mathcal{R}(t)$ during evaporation-condensation of the thin film, as well as for the forms (44) and (46) taken by the first and second laws.

Consider a thin film composed of n chemical species and undergoing evaporation-condensation upon exposure to a vapor of its constituents and possibly a carrier gas. Specifically, we examine the subprocess by which δN_i

moles of the i th species ($i = 1, \dots, n$) condense on or evaporate from the thin film during the time interval $[t, t + \delta t]$, where $\delta N_i > 0$ whenever the i th species condenses on the film and, conversely, $\delta N_i < 0$ when it evaporates from it. *We take as the thermodynamic system under consideration the union of the thin film and the collection of evaporating or condensing molecules present in the vapor during the subprocess in question.* The vapor is assumed to be a mixture of ideal gases. We write $\delta N = \sum_{i=1}^n \delta N_i$ for the total number of moles undergoing evaporation or condensation and recall that w_i denotes the molar mass of the i th species.

Let N_i and ρ_i be the mole number and areal mass density of the i th species in the film, and denote by $N = \sum_{i=1}^n N_i$ the total mole number of the film. Moreover, let $\mathbf{v}$ be the velocity of the film and denote by $\mathbf{u}_i$ the velocity of those molecules of the i th species that have just evaporated or are about to condense and are in the vicinity of the film. For the purpose of the present thermodynamic analysis, both $\mathbf{v}$ and $\mathbf{u}_i$ are assumed uniform. (This assumption is relaxed in the continuum-mechanical formulation of Sections V through VII.) Further, let $\bar{\varepsilon}(\vec{\rho}) := \bar{\varepsilon}(\rho_1, \dots, \rho_n)$ be the internal energy per mole of the film and denote by $\bar{\varepsilon}_i^v$ the internal energy per mole of the i th species in the vapor mixture.

At time t , prior to evaporation-condensation, the internal energy $U(t)$ of the system is given by

$$U(t) = N\bar{\varepsilon}(\vec{\rho}) + \frac{1}{2} \sum_{i=1}^n (\delta N_i + |\delta N_i|) \bar{\varepsilon}_i^v \quad (\text{C.1})$$

and its kinetic energy $K(t)$ is represented by

$$K(t) = \frac{1}{2} \sum_{i=1}^n w_i N_i |\mathbf{v}|^2 + \frac{1}{4} \sum_{i=1}^n w_i (\delta N_i + |\delta N_i|) |\mathbf{u}_i|^2. \quad (\text{C.2})$$

At time $t + \delta t$, after evaporation-condensation has occurred, the internal energy $U(t + \delta t)$ of the system takes the form

$$U(t + \delta t) = (N + \delta N) \bar{\varepsilon}(\vec{\rho} + \delta \vec{\rho}) - \frac{1}{2} \sum_{i=1}^n (\delta N_i - |\delta N_i|) \bar{\varepsilon}_i^v, \quad (\text{C.3})$$

where we use the notation

$$\bar{\varepsilon}(\vec{\rho} + \delta \vec{\rho}) = \bar{\varepsilon}(\rho_1 + \delta \rho_1, \dots, \rho_n + \delta \rho_n) \quad (\text{C.4})$$

and, recalling the convention introduced above, $\delta N_i < 0$ whenever the i th species is evaporating. Similarly the kinetic energy of the thermodynamic system is now given

by

$$K(t + \delta t) = \frac{1}{2} \sum_{i=1}^n w_i (N_i + \delta N_i) |\mathbf{v} + \delta \mathbf{v}|^2 - \frac{1}{4} \sum_{i=1}^n w_i (\delta N_i - |\delta N_i|) |\mathbf{u}_i|^2. \quad (\text{C.5})$$

Here, $\delta \mathbf{v}$ is the change in the velocity of the film that accompanies evaporation-condensation.

We write

$$\delta U = U(t + \delta t) - U(t) \quad (\text{C.6})$$

for the change in the internal energy of the system and

$$\delta K = K(t + \delta t) - K(t) \quad (\text{C.7})$$

for the change in its kinetic energy, with both changes resulting solely from evaporation-condensation.

The expression for the work W done on the system requires some explanation. To arrive at this expression, let us first consider the special case where the thin film and the vapor are all of the same pure substance. Let p be the pressure and v the molar volume of the vapor. Suppose δN mole of the vapor condense on the thin film during the subprocess of interest. The condensed molecules, which constitute a part of the system under consideration and occupy a volume $\delta N v$ at the beginning of the subprocess, are squeezed at the end to zero volume (in our two-dimensional thin-film model) by an environment of constant pressure p . Thus the work done on the condensed molecules by the environment is given by

$$W = \delta N p v. \quad (\text{C.8})$$

We assume that the area of the two-dimensional film is constant throughout the subprocess in question. Then the pressure in the film remains workless and (C.8) gives the expression for the work done on the system as a whole for the subprocess under consideration. (This assumption is relaxed in the continuum-mechanical formulation of Sections V through VII.)

Next, consider a modified version of the previous case where there is now a carrier gas mixed with the vapor of the pure substance. The carrier gas is not part of the thermodynamic system under consideration. While the pressure of the mixture is p , the pressure in the vapor of the pure substance is p^v , its partial pressure. In this case, the work done on the condensed molecules during the subprocess is

$$W = \delta N p^v v^v, \quad (\text{C.9})$$

where v^v is the molar volume of the vapor of pure substance. A moment's thought will convince the reader that (C.8) and (C.9) remain valid if the aforementioned examples are those of evaporation rather than condensation; the difference is only that $\delta N < 0$ for evaporation, whereas $\delta N > 0$ for condensation.

For the general case, where the pressure acting on the vapor of the i th species is its partial pressure p_i^v , the work done on the part of the system that consists of the condensing or evaporating molecules is given by

$$W = \sum_{i=1}^n \delta N_i p_i^v v_i^v, \quad (\text{C.10})$$

where v_i^v is the molar volume of the i th species. Similar to our discussion of the special case (C.8) above, (C.10) will also give the expression for the work done on the system as a whole if we assume that the area of the two-dimensional film remains constant during the subprocess under consideration.

The heat Q received by the system can be written as

$$Q = \mathcal{Q}_s \delta t, \quad (\text{C.11})$$

with $\mathcal{Q}_s$ the heating (i.e., heat supply per unit time) that accompanies evaporation-condensation.

The first law then takes the form

$$\delta U + \delta K = W + Q, \quad (\text{C.12})$$

with δU given by (C.1), (C.3), and (C.6); δK by (C.2), (C.5), and (C.7); W by (C.10); and Q by (C.11).

As $\delta t \rightarrow 0$, (C.1), (C.3), and (C.6) yield an expression,

$$\dot{U} = \frac{d}{dt}(N\bar{\varepsilon}) - \dot{N}_i \bar{\varepsilon}_i^v, \quad (\text{C.13})$$

for the temporal rate of change of the internal energy U of the system, where the superposed dot denotes differentiation with respect to time and summation over the repeated index i is implied.

Similarly, (C.2), (C.5), and (C.7) deliver the expression

$$\dot{K} = \frac{d}{dt} \left(\frac{1}{2} \sum_{i=1}^n N_i w_i |\mathbf{v}|^2 \right) - \frac{1}{2} \sum_{i=1}^n \dot{N}_i w_i |\mathbf{u}_i|^2 \quad (\text{C.14})$$

for the temporal rate of change of the kinetic energy K of the system.

Hence, in view of (C.10), (C.11), (C.13), and (C.14), the first law (C.12) reduces to

$$\begin{aligned} \frac{d}{dt} \left(N\bar{\varepsilon} + \frac{1}{2} \sum_{i=1}^n w_i N_i |\mathbf{v}|^2 \right) &= \sum_{i=1}^n \dot{N}_i p_i^v v_i^v \\ &+ \sum_{i=1}^n \dot{N}_i \bar{\varepsilon}_i^v + \frac{1}{2} \sum_{i=1}^n \dot{N}_i w_i |\mathbf{u}_i|^2 + \mathcal{Q}_s, \end{aligned} \quad (\text{C.15})$$

as $\delta t \rightarrow 0$. Equation (C.15) embodies the first law as it applies to the system under consideration. It may be written in the form

$$\dot{\mathcal{E}}_f = \mathcal{P}_s + \mathcal{F}_f + \mathcal{Q}_s, \quad (\text{C.16})$$

where

$$\mathcal{E}_f = N\bar{\varepsilon} + \frac{1}{2} \sum_{i=1}^n N_i w_i |\mathbf{v}|^2 \quad (\text{C.17})$$

is the total (internal + kinetic) energy of the film,

$$\mathcal{P}_s = \sum_{i=1}^n \dot{N}_i p_i^v v_i^v \quad (\text{C.18})$$

is the rate of work being done on the system, and

$$\mathcal{F}_f = \sum_{i=1}^n \dot{N}_i \bar{\varepsilon}_i^v + \frac{1}{2} \sum_{i=1}^n \dot{N}_i w_i |\mathbf{u}_i|^2 \quad (\text{C.19})$$

is the flow of internal and kinetic energies into the film as it condenses or out of the film as it evaporates. One crucial point in the foregoing thermodynamic analysis, which delivers (C.15), is that the system at time t includes the thin film as well as the molecules condensing on or evaporating from it.

Next, let $\bar{\eta}(\vec{\varrho}) := \bar{\eta}(\varrho_1, \dots, \varrho_n)$ denote the entropy per mole of the film and $\bar{\eta}_i^v$ its counterpart for the i th species in the vapor. At time t , prior to evaporation-condensation, the net entropy $S(t)$ of the system is given by

$$S(t) = N\bar{\eta}(\vec{\varrho}) + \frac{1}{2} \sum_{i=1}^n (\delta N_i + |\delta N_i|) \bar{\eta}_i^v, \quad (\text{C.20})$$

whereas, at time $t + \delta t$, after evaporation-condensation has taken place, the total entropy $S(t + \delta t)$ has the form

$$\begin{aligned} S(t + \delta t) &= (N + \delta N) \bar{\eta}(\vec{\varrho} + \delta \vec{\varrho}) \\ &- \frac{1}{2} \sum_{i=1}^n (\delta N_i - |\delta N_i|) \bar{\eta}_i^v, \end{aligned} \quad (\text{C.21})$$

where

$$\bar{\eta}(\vec{\varrho} + \delta \vec{\varrho}) = \bar{\eta}(\varrho_1 + \delta \varrho_1, \dots, \varrho_n + \delta \varrho_n). \quad (\text{C.22})$$

The second law as it applies to the thermodynamic system under consideration takes the form

$$\delta S \geq \frac{1}{\Theta} \mathcal{Q}_s \delta t, \quad (\text{C.23})$$

where Θ is the temperature and

$$\delta S = S(t + \delta t) - S(t) \quad (\text{C.24})$$

is the change in total entropy due to evaporation or condensation.

As $\delta t \rightarrow 0$, (C.23) reduces to

$$\frac{d}{dt}(N\bar{\eta}) \geq \sum_{i=1}^n \bar{\eta}_i^v \dot{N}_i + \frac{\mathcal{Q}_s}{\Theta} \quad (\text{C.25})$$

or, equivalently,

$$\dot{S}_f \geq \mathcal{H}_f + \frac{\mathcal{Q}_s}{\Theta}, \quad (\text{C.26})$$

where

$$S_f = N\bar{\eta} \quad (\text{C.27})$$

is the entropy of the film and

$$\mathcal{H}_f = \sum_{i=1}^n \bar{\eta}_i^v \dot{N}_i \quad (\text{C.28})$$

is the flow of entropy into or out of the film that results from condensation or evaporation.

Assuming that the process is isothermal (i.e., Θ is constant), (C.25) can be rewritten as

$$-\frac{d}{dt}(\Theta N \bar{\eta}) \leq -\sum_{i=1}^n \Theta \bar{\eta}_i^v \dot{N}_i - \mathcal{Q}_s. \quad (\text{C.29})$$

Hence, on combining (C.15) and (C.29), we obtain the energy imbalance

$$\frac{d}{dt} \left(N \bar{\psi} + \frac{1}{2} \sum_{i=1}^n N_i w_i |\mathbf{v}|^2 \right) \leq \sum_{i=1}^n \dot{N}_i \bar{\mu}_i^v + \frac{1}{2} \sum_{i=1}^n \dot{N}_i w_i |\mathbf{u}_i|^2, \quad (\text{C.30})$$

where

$$\bar{\psi} = \bar{\varepsilon} - \Theta \bar{\eta} \quad (\text{C.31})$$

is the molar free energy of the film and

$$\bar{\mu}_i^v = \bar{\varepsilon}_i^v - \Theta \bar{\eta}_i^v + p_i^v v_i^v \quad (\text{C.32})$$

is the partial Gibbs free energy of the i th species in the vapor.

-
- [1] C. N. Hoth, S. A. Choulis, P. Schilinsky, and C. J. Brabec, *Adv. Mater.* **19**, 3973 (2007).
- [2] S. S. Lee and Y.-L. Loo, *Annu. Rev. Chem. Biomol. Eng.* **1**, 59 (2010).
- [3] S. R. Forrest, *Nature* **428**, 911 (2004).
- [4] Y.-L. Loo, *Am. Instit. Chem. Engineers* **53**, 1066 (2007).
- [5] J. M. Mativetsky and Y.-L. Loo, *Am. Instit. Chem. Engineers* **58**, 3280 (2012).
- [6] M. T. Lloyd, J. E. Anthony, and G. G. Malliaras, *Materials Today* **10**, Number 11, 34 (2007).
- [7] M. T. Lloyd, A. C. Mayer, S. Subramanian, D. A. Mourey, D. J. Herman, A. V. Bapat, J. E. Anthony, and G. G. Malliaras, *J. Am. Chem. Soc.* **129**, 9144 (2007).
- [8] S. S. Lee, S. Muralidharan, A. R. Woll, M. A. Loth, J. E. Anthony, M. Haataja, and Y.-L. Loo, *Chem. Mater.* **24**, 2920 (2012).
- [9] S. S. Lee, C. S. Kim, E. D. Gomez, B. Purushothaman, M. F. Toney, C. Wang, A. Hexemer, J. E. Anthony, and Y.-L. Loo, *Adv. Mater.* **21**, 3605 (2009).
- [10] B. A. Gregg, *J. Phys. Chem.* **100**, 852 (1996).
- [11] K. C. Dickey, J. E. Anthony, and Y.-L. Loo, *Adv. Mater.* **18**, 1721 (2006).
- [12] S. Miller, G. Franchini, Y.-Y. Lin, C. Li, C.-W. Chen, W.-F. Su, and M. Chhowalla, *J. Mater. Chem.* **18**, 306 (2008).
- [13] H. Chen, S. Hu, H. Zang, B. Hu, and M. Dadmun, *Adv. Func. Mater.* **23**, 1701 (2013).
- [14] H. U. Khan, R. Li, Y. Ren, L. Chen, M. M. Payne, U. S. Bhansali, D.-M. Smilgies, J. E. Anthony, and A. Amassian, *ACS Appl. Mater. Interfaces* **5**, 2325 (2013).
- [15] R. Hegde, N. Henry, B. Whittle, H. Zang, B. Hu, J. Chen, K. Xiao, and M. Dadmun, *Solar Ener. Mater. & Solar Cells* **107**, 112 (2012).
- [16] S. S. Lee, S. B. Tang, D.-M. Smilgies, A. R. Woll, M. A. Loth, J. M. Mativetsky, J. E. Anthony, and Y.-L. Loo, *Adv. Mater.* **24**, 2692 (2012).
- [17] Y.-L. Loo (private communication, 2012).
- [18] P. F. James, *Advances in Ceramics*, vol. 4, eds. J. H. Simmons, D. R. Uhlmann and G. H. Beagle (American Ceramic Society, Westerville, 1982) p. 1.
- [19] U. Köster, U. Herold, *Glassy Metals I*, eds. J. H. Güntherodt and H. Beck, vol. 46 *Topics in Appl. Phys.* (Springer, Berlin, 1981) p. 225.
- [20] H. W. Morse, C. H. Warren, and J. D. H. Donnay, *Am. J. Sci.*, series 5, **23**, 421 (1932).
- [21] H. W. Morse, J. D. H. Donnay, *Am. J. Sci.*, series 5, **23**, 440 (1932).
- [22] J. H. Magill, *J. Mater. Sci.* **36**, 3143 (2001).
- [23] J. H. Magill, D. J. Plazek, *J. Chem. Phys.* **46**, 3757 (1967).
- [24] J. L. Hutter, J. Bechhoefer, *Phys. Rev. E* **59**, 4342 (1999).
- [25] H. D. Keith and F. J. Padden, Jr., *J. Appl. Phys.* **34**, 2409 (1963).
- [26] N. Goldenfeld, *J. Crystal Growth* **84**, 601 (1987).
- [27] L. Gránásy, T. Pusztai, G. Tegze, J. A. Warren, and J. F. Douglas, *Phys. Rev. E* **72**, 011605 (2005).
- [28] C.-S. Man, M. Jabbour, R. Paroni, Y.-L. Loo, S. S. Lee, J. E. Anthony, and M. A. Loth, *in preparation* (2013).
- [29] J. W. Bruce and P. J. Giblin, *Curves and Singularities* (Cambridge University Press, Cambridge, 1984) pp. 26–28.
- [30] A. N. Beris and B. J. Edwards, *Thermodynamics of Flowing Systems: with Internal Microstructure* (Oxford University Press, New York, 1994) p. 80.
- [31] Y. S. Chung, N. Shin, J. Kang, Y. Jo, V. M. Prabhu, S. K. Satija, R. J. Kline, D. M. DeLongchamp, M. F. Toney, M. A. Loth, B. Purushothaman, J. E. Anthony, and D. Y. Yoon, *J. Am. Chem. Soc.* **133**, 412 (2011).